



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 0 958 298 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
07.05.2003 Bulletin 2003/19

(51) Int Cl.7: **C07F 7/18, C08J 5/08,
C08K 5/54**

(21) Application number: **98941025.3**

(86) International application number:
PCT/US98/17391

(22) Date of filing: **21.08.1998**

(87) International publication number:
WO 99/009036 (25.02.1999 Gazette 1999/08)

(54) **BLOCKED MERCAPTOSILANE COUPLING AGENTS FOR FILLED RUBBERS**

**BLOCKIERTE MERKAPTOSILANE ALS KUPPLUNGSMITTEL FÜR GEFÜLLTE
KAUTSCHUKZUSAMMENSETZUNG**

**AGENTS DE COUPLAGE A BASE DE MERCAPTOSILANES BLOQUES, UTILISES DANS DES
CAOUTCHOUCS A CHARGE**

(84) Designated Contracting States:
AT BE DE ES FI FR GB IE IT LU NL PT SE

(30) Priority: **21.08.1997 US 56566**

(43) Date of publication of application:
24.11.1999 Bulletin 1999/47

(60) Divisional application:
02019729.9 / 1 270 581

(73) Proprietor: **Crompton Corporation
Middlebury, Connecticut 06749 (US)**

(72) Inventors:
• **CRUSE, Richard, W.**
Yorktown Heights, NY 10598 (US)
• **PICKWELL, Robert, J.**
Tonawanda, NY 14150 (US)
• **WELLER, Keith, J.**
Yonkers, NY 10703 (US)
• **POHL, Eric, R.**
Mt. Kisco, NY 10549 (US)

(74) Representative:
**Wibbelmann, Jobst, Dr., Dipl.-Chem. et al
Wuesthoff & Wuesthoff,
Patent- und Rechtsanwälte,
Schweigerstrasse 2
81541 München (DE)**

(56) References cited:
**EP-A- 0 784 072 DE-A- 2 508 931
DE-A- 3 813 678 US-A- 3 692 812
US-A- 3 922 436**

- **CHEMICAL ABSTRACTS, vol. 111, no. 10, 4
September 1989 Columbus, Ohio, US; abstract
no. 79474, ITO, K. ET AL.: "epoxy resin potting
compositions for semiconductor devices"
XP002084435 & JP 63 248821 A (SHIN-ETSU
CHEMICAL INDUSTRY CO., LTD)**
- **GORNOWICZ, G.A. ET AL.: "preparation of
silylalkanethiols" THE JOURNAL OF ORGANIC
CHEMISTRY, vol. 33, no. 7, 1968, pages
2918-2924, XP002084433**
- **VORONKOV, M.G. ET AL.:
"trialkoxysilylalkanethiol and
bis(trialkoxysilylalkyl) sulfides" IZVESTIYA
AKADEMII NAUK SSSR, no. 8, 1977, pages
1849-1851, XP002084434**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 0 958 298 B1

Description

FIELD OF THE INVENTION

5 [0001] The invention relates to the manufacture of rubbers including inorganic fillers and silane coupling agents.

BACKGROUND

10 [0002] The majority of prior art in the use of sulfur-containing coupling agents in rubber involves silanes containing one or more of the following chemical bonds types: S-H (mercapto), S-S (disulfide or polysulfide), or C=S (thiocarbonyl). Mercaptosilanes have offered superior coupling at substantially reduced loadings; however, their high chemical reactivity with organic polymers leads to unacceptably high viscosities during processing and premature curing (scorch). Their undesirability is aggravated by their odor. As a result, other, less reactive coupling agents have been found. Hence, a compromise must be found between coupling and the associated final properties, processability, and required loading levels, which invariably leads to the need to use substantially higher coupling agent loadings than would be required with mercaptosilanes, and often also to the need to deal with less than optimal processing conditions, both of which lead to higher costs.

15 [0003] The prior art discloses acylthioalkyl silanes, such as $\text{CH}_3\text{C}(=\text{O})\text{S}(\text{CH}_2)_{1-3}\text{Si}(\text{OR})_3$ [M.G. Voronkov et al. in *Inst. Org. Khim.*, Irkutsk, Russia] and $\text{HOC}(=\text{O})\text{CH}_2\text{CH}_2\text{C}(=\text{O})\text{S}(\text{CH}_2)_3\text{Si}(\text{OC}_2\text{H}_5)_3$ [US Patent No. 3,922,436 to R. Bell et al.]. Takeshita and Sugawara disclosed in Japanese Patent JP 63270751A2 the use of compounds represented by the general formula, $\text{CH}_2=\text{C}(\text{CH}_3)\text{C}(=\text{O})\text{S}(\text{CH}_2)_{1-6}\text{Si}(\text{OCH}_3)_3$ in tire tread compositions, but these compounds are not desirable because the unsaturation α,β to the carbonyl group of the thioester has the undesirable potential to polymerize during the compounding process or during storage.

20 [0004] Prior art by Yves Bomal and Olivier Durel, in Australian Patent AU-A-10082/97 (EP-A-784072), discloses the use in rubber of silanes of the structure represented by $\text{R}^1_n\text{X}_{3-n}\text{Si}(\text{Alk})_m(\text{Ar})_p\text{-S}(\text{C}=\text{O})\text{-R}$ where R^1 is phenyl or alkyl; X is halogen, alkoxy, cycloalkoxy, acyloxy, or OH; Alk is alkyl; Ar is aryl; R is alkyl, alkenyl, or aryl; n is 0 to 2; and m and p are each 0 or 1, but not both zero. This prior art, however, stipulates that compositions of the structures of Formula (1P) must be used in conjunction with functionalized siloxanes. In addition, the prior art does not disclose nor suggest the use of compounds of Formula (1P) as latent mercaptosilane coupling agents, nor does it disclose nor suggest the use of these compounds in any way which would give rise to the advantages of using them as a source of latent mercaptosilane.

25 [0005] US Patent Nos. 4,519,430 to Ahamd et al. and 4,184,998 to Shippey et al. disclose the blocking of a mercaptosilane with an isocyanate to form a solid which is added to a tire composition, which mercaptan reacts into the tire during heating, which could happen at any time during processing since this a thermal mechanism. The purpose of this silane is to avoid the sulfur smell of the mercaptosilane, not to improve the processing of the tire. Moreover, the isocyanate used has toxicity issues, when used to make the silane and when released during rubber processing.

30 [0006] U.S. Patent No. 3,957,718 to Porchet et al. discloses compositions containing silica, phenoplasts or aminoplasts and silanes such as xanthates, thioxanthates and dithiocarbamates; however, the prior art does not disclose nor suggest the use of these silanes as latent mercaptosilane coupling agents nor as the advantage of using them as a source of latent mercaptosilane. There remains a need for effective latent coupling agents which exhibit the advantages of mercaptosilanes without exhibiting the disadvantages such as described herein. DE 3813678 A discloses a process for the manufacture of rubber.

SUMMARY OF THE INVENTION

45 [0007] The present invention teaches a process for the manufacture of a filled rubber comprising:

- a. mixing a rubber, a blocked mercaptosilane and an inorganic filler;
- 50 b. mixing into the mixture of step (a) a deblocking agent to the mixture to deblock the mercaptosilane and a curing agent; and
- c. allowing the mixture to cure. Further embodiments of the invention are set forth in the claims dependent on the main claim.

55 The silanes to be used in the present invention are mercaptosilane derivatives in which the mercapto group is blocked ("blocked mercaptosilanes"), i.e., the mercapto hydrogen atom is replaced by another group (hereafter referred to as "blocking group"). Specifically, the silanes are blocked mercaptosilanes in which the blocking group contains an unsaturated heteroatom or carbon chemically bound directly to sulfur via a single bond. This blocking group optionally may be substituted with one or more carboxylate ester or carboxylic acid functional groups. The use of these silanes

in the manufacture of inorganic filled rubbers is taught wherein they are deblocked by the use of a deblocking agent during the manufacturing process.

DETAILED DESCRIPTION OF THE INVENTION

Silane Structures

[0008] The blocked mercaptosilanes can be represented by the Formulae (1-2);



wherein

Y is a polyvalent species $(\text{Q})_z\text{A}(=\text{E})$, preferably selected from the group consisting of $-\text{C}(=\text{NR})-$; $-\text{SC}(=\text{NR})-$; $-\text{SC}(=\text{O})-$; $-(\text{NR})\text{C}(=\text{O})-$; $-(\text{NR})\text{C}(=\text{S})-$; $-\text{OC}(=\text{O})-$; $-\text{OC}(=\text{S})-$; $-\text{C}(=\text{O})-$; $-\text{SC}(=\text{S})-$; $-\text{C}(=\text{S})-$; $-\text{S}(=\text{O})_2-$; $-\text{OS}(=\text{O})_2-$; $-(\text{NR})\text{S}(=\text{O})_2-$; $-\text{SS}(=\text{O})-$; $-\text{OS}(=\text{O})-$; $-(\text{NR})\text{S}(=\text{O})-$; $-\text{SS}(=\text{O})_2-$; $-(\text{S})_2\text{P}(=\text{O})-$; $-(\text{S})\text{P}(=\text{O})-$; $-\text{P}(=\text{O})(\text{O})_2-$; $-(\text{S})_2\text{P}(=\text{S})-$; $-(\text{S})\text{P}(=\text{S})-$; $-\text{P}(=\text{S})(\text{O})_2-$; $-(\text{NR})_2\text{P}(=\text{O})-$; $-(\text{NR})(\text{S})\text{P}(=\text{O})-$; $-(\text{O})(\text{NR})\text{P}(=\text{O})-$; $-(\text{O})(\text{S})\text{P}(=\text{O})-$; $-(\text{O})_2\text{P}(=\text{O})-$; $-(\text{O})\text{P}(=\text{O})-$; $-(\text{NR})\text{P}(=\text{O})-$; $-(\text{NR})_2\text{P}(=\text{S})-$; $-(\text{NR})(\text{S})\text{P}(=\text{S})-$; $-(\text{O})(\text{NR})\text{P}(=\text{S})-$; $-(\text{O})(\text{S})\text{P}(=\text{S})-$; $-(\text{O})_2\text{P}(=\text{S})-$; $-(\text{O})\text{P}(=\text{S})-$; and $-(\text{NR})\text{P}(=\text{S})-$; each wherein the atom (A) attached to the unsaturated heteroatom (E) is attached to the sulfur, which in turn is linked via a group G to the silicon atom;

each R is chosen independently from hydrogen, straight, cyclic or branched alkyl that may or may not contain unsaturation, alkenyl groups, aryl groups, and aralkyl groups, with each R containing from 1 to 18 carbon atoms;

each G is independently a monovalent or polyvalent group derived by substitution of alkyl, alkenyl, aryl or aralkyl wherein G can contain from 1 to 18 carbon atoms, with the proviso that G is not such that the silane would contain an α,β -unsaturated carbonyl including a carbon-carbon double bond next to the thiocarbonyl group, and if G is univalent (i.e., if $p = 0$), G can be a hydrogen atom;

X is independently a group selected from the group consisting of $-\text{Cl}$, $-\text{Br}$, $\text{RO}-$, $\text{RC}(=\text{O})\text{O}-$, $\text{R}_2\text{C}=\text{NO}-$, $\text{R}_2\text{NO}-$ or $\text{R}_2\text{N}-$, $-\text{R}$, $-(\text{OSiR}_2)_i(\text{OSiR}_3)_j$ wherein each R and G is as above and at least one X is not $-\text{R}$;

Q is oxygen, sulfur or $-(\text{NR})-$;

A is carbon, sulfur, phosphorus, or sulfonyl;

E is oxygen, sulfur or NR;

p is 0 to 5; r is 1 to 3; z is 0 to 2; q is 0 to 6; a is 0 to 7; b is 1 to 3; j is 0 to 1, but it may be 0 only if p is 1, c is 1 to 6, preferably 1 to 4; t is 0 to 5; s is 1 to 3; k is 1 to 2, with the provisos that (A) if A is carbon, sulfur or sulfonyl, then (i) $a + b = 2$ and (ii) $k = 1$; (B) if A is phosphorus, then $a + b = 3$ unless both (i) $c > 1$ and (ii) $b = 1$, in which case $a = c + 1$; and (C) if A is phosphorus, then $k = 2$.

[0009] As used herein, "alkyl" includes straight, branched and cyclic alkyl groups, and "alkenyl" includes straight, branched and cyclic alkenyl groups containing one or more carbon-carbon double bonds. Specific alkyls include methyl, ethyl, propyl, isobutyl, and specific aralkyls include phenyl, tolyl and phenethyl. As used herein, "cyclic alkyl" or "cyclic alkenyl" also includes bicyclic and higher cyclic structures, as well as cyclic structures further substituted with alkyl groups. Representative examples include norbornyl, norbornenyl, ethylnorbornyl, ethylnorbornenyl, ethylcyclohexyl, ethylcyclohexenyl, and cyclohexylcyclohexyl.

[0010] Representative examples of the functional groups $(-\text{YS}-)$ present in the silanes of the present invention include thiocarboxylate ester, $-\text{C}(=\text{O})-\text{S}-$ (any silane with this functional group is a "thiocarboxylate ester silane"); dithiocarboxylate, $-\text{C}(=\text{S})-\text{S}-$ (any silane with this functional group is a "dithiocarboxylate ester silane"); thiocarbonate ester, $-\text{O}-\text{C}(=\text{O})-\text{S}-$ (any silane with this functional group is a "thiocarbonate ester silane"); dithiocarbonate ester, $-\text{S}-\text{C}(=\text{O})-\text{S}-$ and $-\text{O}-\text{C}(=\text{S})-\text{S}-$ (any silane with this functional group is a "dithiocarbonate ester silane"); trithiocarbonate ester, $-\text{S}-\text{C}(=\text{S})-\text{S}-$ (any silane with this functional group is a "trithiocarbonate ester silane"); dithiocarbamate ester, $\text{N}-\text{C}(=\text{S})-\text{S}-$ (any silane with this functional group is a "dithiocarbamate ester silane"); thiosulfonate ester, $-\text{S}(=\text{O})_2-\text{S}-$ (any silane with this functional group is a "thiosulfonate ester silane"); thiosulfate ester, $-\text{O}-\text{S}(=\text{O})_2-\text{S}-$ (any silane with this functional group is a "thiosulfate ester silane"); thiosulfamate ester, $-(\text{N})-\text{S}(=\text{O})_2-\text{S}-$ (any silane with this functional group is a "thiosulfamate ester silane"); thiosulfinate ester, $\text{C}-\text{S}(=\text{O})-\text{S}-$ (any silane with this functional group is a "thiosulfinate ester silane"); thiosulfite ester, $-\text{O}-\text{S}(=\text{O})-\text{S}-$ (any silane with this functional group is a "thiosulfite ester silane"); thiosulfimate ester, $\text{N}-\text{S}(=\text{O})-\text{S}-$ (any silane with this functional group is a "thiosulfimate ester silane"); thiophosphate ester, $\text{P}(=\text{O})(\text{O})_2-\text{S}-$ (any silane with this functional group is a "thiophosphate ester silane"); dithiophosphate ester, $\text{P}(=\text{O})$

(O-)(S-)₂ or P(=S)(O-)₂(S-) (any silane with this functional group is a "dithiophosphate ester silane"); trithiophosphate ester, P(=O)(S-)₃ or P(=S)(O-)(S-)₂ (any silane with this functional group is a "trithiophosphate ester silane"); tetrathiophosphate ester P(=S)(S-)₃ (any silane with this functional group is a "tetrathiophosphate ester silane"); thiophosphamate ester, -P(=O)(-N-)(S-) (any silane with this functional group is a "thiophosphamate ester silane"); dithiophosphamate ester, -P(=S)(-N-)(S-) (any silane with this functional group is a "dithiophosphamate ester silane"); thiophosphoramidate ester, (-N-)P(=O)(O-)(S-) (any silane with this functional group is a "thiophosphoramidate ester silane"); dithiophosphoramidate ester, (-N-)P(=O)(S-)₂ or (-N-)P(=S)(O-)(S-) (any silane with this functional group is a "dithiophosphoramidate ester silane"); trithiophosphoramidate ester, (-N-)P(=S)(S-)₂ (any silane with this functional group is a "trithiophosphoramidate ester silane").

Novel silanes to be used in the present invention are those wherein Y groups are -C(=NR)-; -SC(=NR)-; -SC(=O)-; -OC(=O)-; -S(=O)-; -S(=O)₂-; -OS(=O)₂-; -(NR)S(=O)₂-; -SS(=O)-; -OS(=O)-; -(NR)S(=O)-; -SS(=O)₂-; (-S)₂P(=O)-; (-S)P(=O)-; -P(=O)(-)-₂; (-S)₂P(=S)-; (-S)P(=S)-; -P(=S)(-)-₂; (-NR)₂P(=O)-; (-NR)(-S)P(=O)-; (-O)(-NR)P(=O)-; (-O)(-S)P(=O)-; (-O)₂P(=O)-; (-O)P(=O)-; (-NR)P(=O)-; (-NR)₂P(=S)-; (-NR)(-S)P(=S)-; (-O)(-NR)P(=S)-; (-O)(-S)P(=S)-; (-O)₂P(=S)-; (-O)P(=S)-; and -(-NR)P(=S)-. Particularly preferred of these are -OC(=O)-; -SC(=O)-; -S(=O)-; -OS(=O)-; -(-S)P(=O)-; and -P(=O)(-)-₂.

[0011] Another novel silane would be one wherein Y is RC(=O)- wherein R has a primary carbon attached to the carbonyl and is a C₂-C₁₂ alkyl, more preferably a C₆-C₈ alkyl.

[0012] Another preferred novel structure is of the form X₃SiGSC(=O)GC(=O)SGSiX₃ wherein G is a divalent hydrocarbon.

[0013] Examples of G include -(CH₂)_n- wherein n is 1 to 12, diethylene cyclohexane, 1,2,4-triethylene cyclohexane, and diethylene benzene. It is preferred that the sum of the carbon atoms within the G groups within the molecule are from 3 to 18, more preferably 6 to 14. This amount of carbon in the blocked mercaptosilane facilitates the dispersion of the inorganic filler into the organic polymers, thereby improving the balance of properties in the cured filled rubber.

[0014] Preferable R groups are alkyls of C₁ to C₄ and H.

[0015] Specific examples of X are methoxy, ethoxy, isobutoxy, propoxy, isopropoxy, acetoxy and oximato. Methoxy, acetoxy and ethoxy are preferred. At least one X must be reactive (i.e., hydrolyzable).

[0016] Preferred embodiments are wherein p is 0 to 2; X is RO- or RC(=O)O-; R are hydrogen, phenyl, isopropyl, cyclohexyl, or isobutyl; G is a substituted phenyl or substituted straight chain alkyl of C₂ to C₁₂. Other preferred embodiments are wherein X is RO, r=1 and s=1. The most preferred embodiments include those wherein p is zero; X is ethoxy and G is a C₃-C₁₂ alkyl derivative.

[0017] Representative examples of the silanes of the present invention include 2-triethoxysilyl-1-ethyl thioacetate; 2-trimethoxysilyl-1-ethyl thioacetate; 2-(methyldimethoxysilyl)-1-ethyl thioacetate; 3-trimethoxysilyl-1-propyl thioacetate; triethoxysilylmethyl thioacetate; trimethoxysilylmethyl thioacetate; trisopropoxysilylmethyl thioacetate; methyldiethoxysilylmethyl thioacetate; methyldimethoxysilylmethyl thioacetate; methyldiisopropoxysilylmethyl thioacetate; dimethylethoxysilylmethyl thioacetate; dimethylmethoxysilylmethyl thioacetate; dimethylisopropoxysilylmethyl thioacetate; 2-triisopropoxysilyl-1-ethyl thioacetate; 2-(methyldiethoxysilyl)-1-ethyl thioacetate; 2-(methyldiisopropoxysilyl)-1-ethyl thioacetate; 2-(dimethylethoxysilyl)-1-ethyl thioacetate; 2-(dimethylmethoxysilyl)-1-ethyl thioacetate; 2-(dimethylisopropoxysilyl)-1-ethyl thioacetate; 3-triethoxysilyl-1-propyl thioacetate; 3-triisopropoxysilyl-1-propyl thioacetate; 3-methyldiethoxysilyl-1-propyl thioacetate; 3-methyldimethoxysilyl-1-propyl thioacetate; 3-methyldiisopropoxysilyl-1-propyl thioacetate; 1-(2-triethoxysilyl-1-ethyl)-4-thioacetylcyclohexane; 1-(2-triethoxysilyl-1-ethyl)-3-thioacetylcyclohexane; 2-triethoxysilyl-5-thioacetylnorbornene; 2-triethoxysilyl-4-thioacetylnorbornene; 2-(2-triethoxysilyl-1-ethyl)-5-thioacetylnorbornene; 2-(2-triethoxysilyl-1-ethyl)-4-thioacetylnorbornene; 1-(1-oxo-2-thia-5-triethoxysilylphenyl)benzoic acid; 6-triethoxysilyl-1-hexyl thioacetate; 1-triethoxysilyl-5-hexyl thioacetate; 8-triethoxysilyl-1-octyl thioacetate; 1-triethoxysilyl-7-octyl thioacetate; 6-triethoxysilyl-1-hexyl thioacetate; 1-triethoxysilyl-5-octyl thioacetate; 8-trimethoxysilyl-1-octyl thioacetate; 1-trimethoxysilyl-7-octyl thioacetate; 10-triethoxysilyl-1-decyl thioacetate; 1-triethoxysilyl-9-decyl thioacetate; 1-triethoxysilyl-2-butyl thioacetate; 1-triethoxysilyl-3-butyl thioacetate; 1-triethoxysilyl-3-methyl-2-butyl thioacetate; 1-triethoxysilyl-3-methyl-3-butyl thioacetate; 3-trimethoxysilyl-1-propyl thioacetate; 3-triethoxysilyl-1-propyl thiopalmitate; 3-triethoxysilyl-1-propyl thiooctoate; 3-triethoxysilyl-1-propyl thiobenzoate; 3-triethoxysilyl-1-propyl thio-2-ethylhexanoate; 3-methyldiacetoxysilyl-1-propyl thioacetate; 3-triacetoxysilyl-1-propyl thioacetate; 2-methyldiacetoxysilyl-1-ethyl thioacetate; 2-triacetoxysilyl-1-ethyl thioacetate; 1-methyldiacetoxysilyl-1-ethyl thioacetate; 1-triacetoxysilyl-1-ethyl thioacetate; tris-(3-triethoxysilyl-1-propyl)trithiophosphate; bis-(3-triethoxysilyl-1-propyl)methyldithiophosphonate; bis-(3-triethoxysilyl-1-propyl)ethyldithiophosphonate; 3-triethoxysilyl-1-propyldimethylthiophosphinate; 3-triethoxysilyl-1-propyldiethylthiophosphinate; tris-(3-triethoxysilyl-1-propyl)tetrathiophosphate; bis-(3-triethoxysilyl-1-propyl)methyltrithiophosphonate; bis-(3-triethoxysilyl-1-propyl)ethyltrithiophosphonate; 3-triethoxysilyl-1-propyldimethyldithiophosphinate; 3-triethoxysilyl-1-propyldiethyldithiophosphinate; tris-(3-methyldimethoxysilyl-1-propyl)trithiophosphate; bis-(3-methyldimethoxysilyl-1-propyl)methyldithiophosphonate; bis-(3-methyldimethoxysilyl-1-propyl)ethyldithiophosphonate; 3-methyldimethoxysilyl-1-propyldimethylthiophosphinate; 3-methyldimethoxysilyl-1-propyldiethylthiophosphinate; 3-triethoxysilyl-1-propylmethylthiosulphate; 3-triethoxysilyl-1-propyl-

methanethiosulphonate; 3-triethoxysilyl-1-propylethanethiosulphonate; 3-triethoxysilyl-1-propylbenzenethiosulphonate; 3-triethoxysilyl-1-propyltoluenethiosulphonate; 3-triethoxysilyl-1-propylnaphthalenethiosulphonate; 3-triethoxysilyl-1-propylxilenethiosulphonate; triethoxysilylmethylmethylthiosulphate; triethoxysilylmethylmethanethiosulphonate; triethoxysilylmethylethanethiosulphonate; triethoxysilylmethylbenzenethiosulphonate; triethoxysilylmethyltoluenethiosulphonate; triethoxysilylmethylnaphthalenethiosulphonate; triethoxysilylmethylxilenethiosulphonate.

[0018] Mixtures of various blocked mercaptosilanes may be used, including wherein synthetic methods result in a distribution of various silanes or where mixes of blocked mercaptosilanes are used for their various blocking or leaving functionalities. Moreover, it is understood that the partial hydrolyzates of these blocked mercaptosilanes (i.e., blocked mercaptosiloxanes) may also be encompassed by the blocked mercaptosilanes herein, in that these partial hydrolyzates will be a side product of most methods of manufacture of the blocked mercaptosilane or can occur upon storage of the blocked mercaptosilane, especially in humid conditions.

[0019] The silane, if liquid, may be loaded on a carrier, such as a porous polymer, carbon black or silica so that it is in solid form for delivery to the rubber. In a preferred mode, the carrier would be part of the inorganic filler to be used in the rubber.

Manufacture of Silanes

[0020] The methods of preparation for blocked mercaptosilanes can involve esterification of sulfur in a sulfur-containing silane and direct incorporation of the thioester group into a silane, either by substitution of an appropriate leaving group or by addition across a carbon-carbon double bond. Illustrative examples of synthetic procedures for the preparation of thioester silanes would include: Reaction 1) the reaction between a mercaptosilane and an acid anhydride corresponding to the thioester group present in the desired product; Reaction 2) reaction of an alkali metal salt of a mercaptosilane with the appropriate acid anhydride or acid halide; Reaction 3) the transesterification between a mercaptosilane and an ester, optionally using any appropriate catalyst such as an acid, base, tin compound, titanium compound, transition metal salt, or a salt of the acid corresponding to the ester; Reaction 4) the transesterification between a thioester silane and another ester, optionally using any appropriate catalyst such as an acid, base, tin compound, titanium compound, transition metal salt, or a salt of the acid corresponding to the ester; Reaction 5) the transesterification between a 1-sila-2-thiacyclopentane or a 1-sila-2-thiacyclohexane and an ester, optionally using any appropriate catalyst such as an acid, base, tin compound, titanium compound, transition metal salt, or a salt of the acid corresponding to the ester; Reaction 6) the free radical addition of a thioacid across a carbon-carbon double bond of an alkene-functional silane, catalyzed by UV light, heat, or the appropriate free radical initiator wherein, if the thioacid is a thiocarboxylic acid, the two reagents are brought into contact with each other in such a way as to ensure that whichever reagent is added to the other is reacted substantially before the addition proceeds; and Reaction 7) the reaction between an alkali metal salt of a thioacid with a haloalkylsilane.

[0021] Acid halides include, but are not limited to, in addition to organic acid halides, inorganic acid halides, such as POT_3 , SOT_2 , SO_2T_2 , COT_2 , CST_2 , PST_3 and PT_5 , wherein T is a halide. Acid anhydrides, include, but are not limited to, in addition to organic acid anhydrides (and their sulfur analogs), inorganic acid anhydrides, such as SO_3 , SO_2 , P_2O_5 , P_2S_5 , $\text{H}_2\text{S}_2\text{O}_7$, CO_2 , COS , and CS_2 .

[0022] Illustrative examples of synthetic procedures for the preparation of thiocarboxylate-functional silanes would include: Reaction 8) the reaction between a mercaptosilane and a carboxylic acid anhydride corresponding to the thiocarboxylate group present in the desired product; Reaction 9) reaction of an alkali metal salt of a mercaptosilane with the appropriate carboxylic acid anhydride or acid halide; Reaction 10) the transesterification between a mercaptosilane and a carboxylate ester, optionally using any appropriate catalyst such as an acid, base, tin compound, titanium compound, transition metal salt, or a salt of the acid corresponding to the carboxylate ester; Reaction 11) the transesterification between a thiocarboxylate-functional silane and another ester, optionally using any appropriate catalyst such as an acid, base, tin compound, titanium compound, transition metal salt, or a salt of the acid corresponding to the other ester; Reaction 12) the transesterification between a 1-sila-2-thiacyclopentane or a 1-sila-2-thiacyclohexane and a carboxylate ester, optionally using any appropriate catalyst such as an acid, base, tin compound, titanium compound, transition metal salt, or a salt of the acid corresponding to the carboxylate ester; Reaction 13) the free radical addition of a thiocarboxylic acid across a carbon-carbon double bond of an alkene-functional silane, catalyzed by UV light, heat, or the appropriate free radical initiator; and Reaction 14) the reaction between an alkali metal salt of a thiocarboxylic acid with a haloalkylsilane.

[0023] Reactions 1 and 8 can be carried out by distilling a mixture of the mercaptosilane and the acid anhydride and optionally a solvent. Appropriate boiling temperatures of the mixture are in the range of 60 to 200 °C; preferably 70 to 170 °C; optionally 50 to 250 °C. This process leads to a chemical reaction in which the mercapto group of the mercaptosilane is esterified to the thioester silane analog with release of an equivalent of the corresponding acid. The acid typically is more volatile than the acid anhydride. The reaction is driven by the removal of the more volatile acid by distillation. For the more volatile acid anhydrides, such as acetic anhydride, the distillation preferably is carried out at

ambient pressure to reach temperatures sufficient to drive the reaction toward completion. For less volatile materials, solvents, such as toluene, xylene, glyme, and diglyme could be used with the process to limit temperature. Alternatively, the process could be run at reduced pressure. It would be useful to use up to a two-fold excess or more of the acid anhydride which would be distilled out of the mixture after all of the more volatile reaction coproducts, consisting of acids and non-silane esters, have been distilled out. This excess of acid anhydride would serve to drive the reaction to completion, as well as to help drive the coproducts out of the reaction mixture. At the completion of the reaction, distillation should be continued to drive out the remaining acid anhydride. The product optionally could be distilled.

[0024] Reactions 2 and 9 can be carried out in two steps. The first step would involve conversion of the mercaptosilane to a corresponding metal derivative. Alkali metal derivatives, especially sodium or also potassium and lithium, are preferable. The metal derivative would be prepared by adding the alkali metal or a strong base derived from the alkali metal to the mercaptosilane. The reaction would occur at ambient temperature. Appropriate bases would include alkali metal alkoxides, amides, hydrides, mercaptides. Alkali metal organometallic reagents would also be effective. Grignard reagents would yield magnesium derivatives which would be another alternative. Solvents, such as toluene, xylene, benzene, aliphatic hydrocarbons, ethers, and alcohols could be used to prepare the alkali metal derivatives. Once the alkali metal derivative is prepared, any alcohol present would need to be removed. This could be done by distillation or evaporation. Alcohols such as methanol, ethanol, propanol, isopropanol, butanol, isobutanol, and t-butanol may be removed by azeotropic distillation with benzene, toluene, xylene, or aliphatic hydrocarbons. Toluene and xylene are preferable; toluene is most preferable. The second step in the overall process would be to add to this solution, with stirring, the acid chloride or acid anhydride at temperatures between -20 °C and the boiling point of the mixture; preferably at temperatures between 0 °C and ambient temperature. The product would be isolated by removing the salt and solvent. It could be purified by distillation.

[0025] Reactions 3 and 10 could be carried out by distilling a mixture of the mercaptosilane and the ester and optionally a solvent and/or a catalyst. Appropriate boiling temperatures of the mixture would be above 100 °C. This process leads to a chemical reaction in which the mercapto group of the mercaptosilane is esterified to the thioester silane analog with release of an equivalent of the corresponding alcohol. The reaction is driven by the removal of the alcohol by distillation, either as the more volatile species, or as an azeotrope with the ester. For the more volatile esters the distillation is suitably carried out at ambient pressure to reach temperatures sufficient to drive the reaction toward completion. For less volatile esters, solvents, such as toluene, xylene, glyme, and diglyme could be used with the process to limit temperature. Alternatively, the process could be run at reduced pressure. It is useful to use up to a two-fold excess or more of the ester, which would be distilled out of the mixture after all of the alcohol coproduct has been distilled out. This excess ester would serve to drive the reaction to completion as well as to help drive the coproduct alcohol out of the reaction mixture. At the completion of the reaction, distillation would be continued to drive out the remaining ester. The product optionally could be distilled.

[0026] Reactions 4 and 11 could be carried out by distilling a mixture of the thioester silane and the other ester and optionally a solvent and/or a catalyst. Appropriate boiling temperatures of the mixture would be above 80 °C; preferably above 100 °C. The temperature would preferably not exceed 250 °C. This process leads to a chemical reaction in which the thioester group of the thioester silane is transesterified to a new thioester silane with release of an equivalent of a new ester. The new thioester silane generally would be the least volatile species present; however, the new ester would be more volatile than the other reactants. The reaction would be driven by the removal of the new ester by distillation. The distillation can be carried out at ambient pressure to reach temperatures sufficient to drive the reaction toward completion. For systems containing only less volatile materials, solvents, such as toluene, xylene, glyme, and diglyme could be used with the process to limit temperature. Alternatively, the process could be run at reduced pressure. It would be useful to use up to a two-fold excess or more of the other ester, which would be distilled out of the mixture after all of the new ester coproduct has been distilled out. This excess other ester would serve to drive the reaction to completion as well as to help drive the coproduct other ester out of the reaction mixture. At the completion of the reaction, distillation would be continued to drive out the remaining said new ester. The product optionally then could be distilled.

[0027] Reactions 5 and 12 could be carried out by heating a mixture of the 1-sila-2-thiacyclopentane or the 1-sila-2-thiacyclohexane and the ester with the catalyst. Optionally, the mixture could be heated or refluxed with a solvent, preferably a solvent whose boiling point matches the desired temperature. Optionally a solvent of higher boiling point than the desired reaction temperature can be used at reduced pressure, the pressure being adjusted to bring the boiling point down to the desired reaction temperature. The temperature of the mixture would be in the range of 80 to 250 °C; preferably 100 to 200 °C. Solvents, such as toluene, xylene, aliphatic hydrocarbons, and diglyme could be used with the process to adjust the temperature. Alternatively, the process could be run under reflux at reduced pressure. The most preferable condition is to heat a mixture of the 1-sila-2-thiacyclopentane or the 1-sila-2-thiacyclohexane and the ester, without solvent, preferably under inert atmosphere, for a period of 20 to 100 hours at a temperature of 120 to 170 °C using the sodium, potassium, or lithium salt of the acid corresponding to the ester as a catalyst. The process leads to a chemical reaction in which the sulfur-silicon bond of the 1-sila-2-thiacyclopentane or the 1-sila-2-thiacy-

clohexane is transesterified by addition of the ester across said sulfur-silicon bond. The product is the thioester silane analog of the original 1-sila-2-thiacyclopentane or the 1-sila-2-thiacyclohexane. Optionally, up to a two-fold excess or more of the ester would be used to drive the reaction toward completion. At the completion of the reaction, the excess ester can be removed by distillation. The product optionally could be purified by distillation.

[0028] Reactions 6 and 13 can be carried out by heating or refluxing a mixture of the alkene-functional silane and the thioacid. Aspects of Reaction 13 have been disclosed previously in US Patent No. 3,692,812 and by G.A. Gomowicz et al. in *J. Org. Chem.* (1968), 33(7), 2918-24. The uncatalyzed reaction can occur at temperatures as low as 105 °C, but often fails. The probability of success increases with temperature and becomes high when the temperature exceeds 160 °C. The reaction may be made reliable and the reaction brought largely to completion by using UV radiation or a catalyst. With a catalyst, the reaction can be made to occur at temperatures below 90 °C. Appropriate catalysts are free radical initiators, e.g., peroxides, preferably organic peroxides, and azo compounds. Examples of peroxide initiators include peracids, such as perbenzoic and peracetic acids; esters of peracids; hydroperoxides, such as t-butyl hydroperoxide; peroxides, such as di-t-butyl peroxide; and peroxy-acetals and ketals, such as 1,1'-bis(t-butylperoxy) cyclohexane, or any other peroxide. Examples of azo initiators include azobisisobutyronitrile (AIBN); 1,1'-azobis(cyclohexanecarbonitrile) (VAZO; DuPont product); and azo-tert-butane. The reaction can be run by heating a mixture of the alkene-functional silane and the thioacid with the catalyst. It is preferable for the overall reaction to be run on an equimolar or near equimolar basis to get the highest conversions. The reaction is sufficiently exothermic that it tends to lead to a rapid temperature increase to reflux followed by a vigorous reflux as the reaction initiates and continues rapidly. This vigorous reaction can lead and hazardous boilovers for larger quantities. Side reactions, contamination and loss in yield can result as well from uncontrolled reactions. The reaction can be controlled effectively by adding partial quantities of one reagent to the reaction mixture, initiating the reaction with the catalyst, allowing the reaction to run its course largely to completion, and then adding the remains of the reagent, either as a single addition or as multiple additives. The initial concentrations and rate of addition and number of subsequent additions of the deficient reagent depend on the type and amount of catalyst used, the scale of the reaction, the nature of the starting materials, and the ability of the apparatus to absorb and dissipate heat. A second way of controlling the reaction would involve the continuous addition of one reagent to the other with concomitant continuous addition of catalyst. Whether continuous or sequential addition is used, the catalyst can be added alone and/or pre-blended with one or both reagents, or combinations thereof. Two methods are preferred for reactions involving thiolacetic acid and alkene-functional silanes containing terminal carbon-carbon double bonds. The first involves initially bringing the alkene-functional silane to a temperature of 160 to 180°C, or to reflux, whichever temperature is lower. The first portion of thiolacetic acid is added at a rate as to maintain up to a vigorous, but controlled reflux. For alkene-functional silanes with boiling points above 100 to 120 °C, this reflux results largely from the relatively low boiling point of thiolacetic acid (88 to 92 °C, depending on purity) relative to the temperature of the alkene-functional silane. At the completion of the addition, the reflux rate rapidly subsides. It often accelerates again within several minutes, especially if an alkene-functional silane with a boiling point above 120 °C is used, as the reaction initiates. If it does not initiate within 10 to 15 minutes, initiation can be brought about by addition of catalyst. The preferred catalyst is di-t-butyl peroxide. The appropriate quantity of catalyst is from 0.2 to 2, preferably from 0.5 to 1 percent of the total mass of mixture to which the catalyst is added. The reaction typically initiates within a few minutes as evidenced by an increase in reflux rate. The reflux temperature gradually increases as the reaction proceeds. When the next portion of thiolacetic acid is added, and the aforementioned sequence of steps are repeated. The preferred number of thiolacetic additions for total reaction quantities of about one to about four kilograms is two, with about one third of the total thiolacetic acid used in the first addition and the remainder in the second. For total quantities in the range of about four to ten kilograms, a total of three thiolacetic additions is preferred, the distribution being approximately 20 percent of the total used in the first addition, approximately 30 percent in the second addition, and the remainder in the third addition. For larger scales involving thiolacetic acid and alkene-functional silanes, it is preferable to use more than a total of three thiolacetic additions and more preferably, to add the reagents in the reverse order. Initially, the total quantity of thiolacetic acid is brought to reflux. This is followed by continuous addition of the alkene-functional silane to the thiolacetic acid at such a rate as to bring about a smooth but vigorous reaction rate. The catalyst, preferably di-t-butylperoxide, can be added in small portions during the course of the reaction or as a continuous flow. It is best to accelerate the rate of catalyst addition as the reaction proceeds to completion to obtain the highest yields of product for the lowest amount of catalyst required. The total quantity of catalyst used should be 0.5 to 2 percent of the total mass of reagents used. Whichever method is used, the reaction is followed up by a vacuum stripping process to remove volatiles and unreacted thiolacetic acid and silane. The product may be purified by distillation.

[0029] Methods to run Reactions 7 and 14 can be carried out in two steps. The first step involves preparation of a salt of the thioacid. Alkali metal derivatives are preferred, with the sodium derivative being most preferred. These salts would be prepared as solutions in solvents in which the salt is appreciably soluble, but suspensions of the salts as solids in solvents in which the salts are only slightly soluble are also a viable option. Alcohols, such as propanol, isopropanol, butanol, isobutanol, and t-butanol, and preferably methanol and ethanol are useful because the alkali

metal salts are slightly soluble in them. In cases where the desired product is alkoxysilanes, it is preferable to use an alcohol corresponding to the silane alkoxy group to prevent transesterification at the silicon ester. Alternatively, non-protic solvents can be used. Examples of appropriate solvents are ethers or polyethers such as glyme, diglyme, and dioxanes; N,N'-dimethylformamide; N,N'-dimethylacetamide; dimethylsulfoxide; N-methylpyrrolidinone; or hexamethylphosphoramide. Once a solution, suspension, or combination thereof of the salt of the thioacid has been prepared, the second step is to react it with the appropriate haloalkylsilane. This may be accomplished by stirring a mixture of the haloalkylsilane with the solution, suspension, or combination thereof of the salt of the thioacid at temperatures corresponding to the liquid range of the solvent for a period of time sufficient to complete substantially the reaction. Preferable temperatures are those at which the salt is appreciably soluble in the solvent and at which the reaction proceeds at an acceptable rate without excessive side reactions. With reactions starting from chloroalkylsilanes in which the chlorine atom is not allylic or benzylic, preferable temperatures are in the range of 60 to 160 °C. Reaction times can range from one or several hours to several days. For alcohol solvents where the alcohol contains four carbon atoms or fewer, the most preferred temperature is at or near reflux. Using diglyme as a solvent, the most preferred temperature is in the range of 70 to 120 °C, depending on the thioacid salt used. If the haloalkylsilane is a bromoalkylsilane or a chloroalkylsilane in which the chlorine atom is allylic or benzylic, temperature reductions of 30 to 60 °C are appropriate relative to those appropriate for nonbenzylic or nonallylic chloroalkylsilanes because of the greater reactivity of the bromo group. Bromoalkylsilanes are preferred over chloroalkylsilanes because of their greater reactivity, lower temperatures required, and greater ease in filtration or centrifugation of the coproduct alkali metal halide. This preference, however, can be overridden by the lower cost of the chloroalkylsilanes, especially for those containing the halogen in the allylic or benzylic position. For reactions between straight chain chloroalkylethoxysilanes and sodium thiocarboxylates to form thiocarboxylate ester ethoxysilanes, it is preferable to use ethanol at reflux for 10 to 20 hours if 5 to 20 % mercaptosilane is acceptable in the product. Otherwise, diglyme would be an excellent choice, in which the reaction would be preferably run in the range of 80 to 120 °C for one to three hours. Upon completion of the reaction, the salts and solvent should be removed and the product may be distilled to achieve higher purity.

[0030] If the salt of the thioacid to be used in Reactions 7 and 14 is not commercially available, its preparation may be accomplished by one of two methods, described below as Method A and Method B. Method A involves adding the alkali metal or a base derived from the alkali metal to the thioacid. The reaction occurs at ambient temperature. Appropriate bases include alkali metal alkoxides, hydrides, carbonate, and bicarbonate. Solvents, such as toluene, xylene, benzene, aliphatic hydrocarbons, ethers, and alcohols may be used to prepare the alkali metal derivatives. In Method B, acid chlorides or acid anhydrides would be converted directly to the salt of the thioacid by reaction with the alkali metal sulfide or hydrosulfide. Hydrated or partially hydrous alkali metal sulfides or hydrosulfides are available, however, anhydrous or nearly anhydrous alkali metal sulfides or hydrosulfides are preferred. Hydrous materials can be used, however, but with loss in yield and hydrogen sulfide formation as a co-product. The reaction involves addition of the acid chloride or acid anhydride to the solution or suspension of the alkali metal sulfide and/or hydrosulfide and heating at temperatures ranging from ambient to the reflux temperature of the solvent for a period of time sufficient to largely complete the reaction, as evidenced by the formation of the co-product salts.

[0031] If the alkali metal salt of the thioacid is prepared in such a way such that an alcohol is present, either because it was used as a solvent, or because it formed, as for example, by the reaction of a thioacid with an alkali metal alkoxide, it may be desirable to remove the alcohol if a product low in mercaptosilane is desired. In this case, it would be necessary to remove the alcohol prior to reaction of the salt of the thioacid with the haloalkylsilane. This could be done by distillation or evaporation. Alcohols such as methanol, ethanol, propanol, isopropanol, butanol, isobutanol, and t-butanol are preferably removed by azeotropic distillation with benzene, toluene, xylene, or aliphatic hydrocarbons. Toluene and xylene are preferable.

Utility

[0032] The blocked mercaptosilanes described herein are useful as coupling agents for organic polymers (i.e., rubbers) and inorganic fillers. The blocked mercaptosilanes are unique in that the high efficiency of the mercapto group can be utilized without the detrimental side effects typically associated with the use of mercaptosilanes, such as high processing viscosity, less than desirable filler dispersion, premature curing (scorch), and odor. These benefits are accomplished because the mercaptan group initially is non-reactive because of the blocking group. The blocking group substantially prevents the silane from coupling to the organic polymer during the compounding of the rubber. Generally, only the reaction of the silane -SiX₃ group with the filler can occur at this stage of the compounding process. Thus, substantial coupling of the filler to the polymer is precluded during mixing, thereby minimizing the undesirable premature curing (scorch) and the associated undesirable increase in viscosity. One can achieve better cured filled rubber properties, such as a balance of high modulus and abrasion resistance, because of the avoidance of premature curing.

[0033] In use, one or more of the blocked mercaptosilanes are mixed with the organic polymer before, during or after the compounding of the filler into the organic polymer. It is preferred to add the silanes before or during the compounding

of the filler into the organic polymer, because these silanes facilitate and improve the dispersion of the filler. The total amount of silane present in the resulting combination should be about 0.05 to about 25 parts by weight per hundred parts by weight of organic polymer (phr); more preferably 1 to 10 phr. Fillers can be used in quantities ranging from about 5 to about 100 phr, more preferably from 25 to 80 phr.

[0034] When reaction of the mixture to couple the filler to the polymer is desired, a deblocking agent is added to the mixture to deblock the blocked mercaptosilane. The deblocking agent may be added at quantities ranging from about 0.1 to about 5 phr; more preferably in the range of from 0.5 to 3 phr. If alcohol or water are present (as is common) in the mixture, a catalyst (e.g., tertiary amines, Lewis acids or thiols) may be used to initiate and promote the loss of the blocking group by hydrolysis or alcoholysis to liberate the corresponding mercaptosilane. Alternatively, the deblocking agent may be a nucleophile containing a hydrogen atom sufficiently labile such that hydrogen atom could be transferred to the site of the original blocking group to form the mercaptosilane. Thus, with a blocking group acceptor molecule, an exchange of hydrogen from the nucleophile would occur with the blocking group of the blocked mercaptosilane to form the mercaptosilane and the corresponding derivative of the nucleophile containing the original blocking group. This transfer of the blocking group from the silane to the nucleophile could be driven, for example, by a greater thermodynamic stability of the products (mercaptosilane and nucleophile containing the blocking group) relative to the initial reactants (blocked mercaptosilane and nucleophile). For example, if the nucleophile were an amine containing an N-H bond, transfer of the blocking group from the blocked mercaptosilane would yield the mercaptosilane and one of several classes of amides corresponding to the type of blocking group used. For example, carboxyl blocking groups deblocked by amines would yield amides, sulfonyl blocking groups deblocked by amines would yield sulfonamides, sulfinyl blocking groups deblocked by amines would yield sulfinamides, phosphonyl blocking groups deblocked by amines would yield phosphonamides, phosphinyl blocking groups deblocked by amines would yield phosphinamides. What is important is that regardless of the blocking group initially present on the blocked mercaptosilane and regardless of the deblocking agent used, the initially substantially inactive (from the standpoint of coupling to the organic polymer) blocked mercaptosilane is substantially converted at the desired point in the rubber compounding procedure to the active mercaptosilane. It is noted that partial amounts of the nucleophile may be used (i.e., a stoichiometric deficiency), if one were to only deblock part of the blocked mercaptosilane to control the degree of vulcanization of a specific formulation.

[0035] Water typically is present on the inorganic filler as a hydrate, or bound to a filler in the form of a hydroxyl group. The deblocking agent could be added in the curative package or, alternatively, at any other stage in the compounding process as a single component. Examples of nucleophiles would include any primary or secondary amines, or amines containing C=N double bonds, such as imines or guanidines; with the proviso that said amine contains at least one N-H (nitrogen-hydrogen) bond. Numerous specific examples of guanidines, amines, and imines well known in the art, which are useful as components in curatives for rubber, are cited in Rubber Chemicals; J. Van Alphen; Plastics and Rubber Research Institute TNO, Delft, Holland; 1973. Some examples include N,N'-diphenylguanidine, N,N',N"-triphenylguanidine, N,N'-di-ortho-tolylguanidine, orthobiguanide, hexamethylenetetramine, cyclohexylethylamine, dibutylamine, and 4,4'-diaminodiphenylmethane. Any general acid catalysts used to transesterify esters, such as Bronsted or Lewis acids, could be used as catalysts.

[0036] The rubber composition need not be, but preferably is, essentially free of functionalized siloxanes, especially those of the type disclosed in Australian Patent AU-A-10082/97, which is incorporated herein by reference. Most preferably the rubber composition is free of functionalized siloxanes.

[0037] In practice, sulfur vulcanized rubber products typically are prepared by thermomechanically mixing rubber and various ingredients in a sequentially step-wise manner followed by shaping and curing the compounded rubber to form a vulcanized product. First, for the aforesaid mixing of the rubber and various ingredients, typically exclusive of sulfur and sulfur vulcanization accelerators (collectively "curing agents"), the rubber(s) and various rubber compounding ingredients typically are blended in at least one, and often (in the case of silica filled low rolling resistance tires) two, preparatory thermomechanical mixing stage(s) in suitable mixers. Such preparatory mixing is referred to as nonproductive mixing or non-productive mixing steps or stages. Such preparatory mixing usually is conducted at temperatures up to 140 °C to 200 °C and often up to 150 °C to 180 °C. Subsequent to such preparatory mix stages, in a final mixing stage, sometimes referred to as a productive mix stage, deblocking agent (in the case of this invention), curing agents, and possibly one or more additional ingredients, are mixed with the rubber compound or composition, typically at a temperature in a range of 50 °C to 130 °C, which is a lower temperature than the temperatures utilized in the preparatory mix stages to prevent or retard premature curing of the sulfur curable rubber, which is sometimes referred to as scorching of the rubber composition. The rubber mixture, sometimes referred to as a rubber compound or composition, typically is allowed to cool, sometimes after or during a process intermediate mill mixing, between the aforesaid various mixing steps, for example, to a temperature of about 50 °C or lower. When it is desired to mold and to cure the rubber, the rubber is placed into the appropriate mold at about at least 130 °C and up to about 200 °C, which will cause the vulcanization of the rubber by the mercapto groups on the mercaptosilane and any other free sulfur sources in the rubber mixture.

[0038] By thermomechanical mixing, it is meant that the rubber compound, or composition of rubber and rubber compounding ingredients, is mixed in a rubber mixture under high shear conditions where it autogeneously heats up as a result of the mixing primarily due to shear and associated friction within the rubber mixture in the rubber mixer. Several chemical reactions may occur at various steps in the mixing and curing processes.

[0039] The first reaction is a relatively fast reaction and is considered herein to take place between the filler and the SiX_3 group of the blocked mercaptosilane. Such reaction may occur at a relatively low temperature such as, for example, at about 120 °C. The second and third reactions are considered herein to be the deblocking of the mercaptosilane and the reaction which takes place between the sulfuric part of the organosilane (after deblocking), and the sulfur vulcanizable rubber at a higher temperature; for example, above about 140 °C.

[0040] Another sulfur source may be used, for example, in the form of elemental sulfur as S_8 . A sulfur donor is considered herein as a sulfur containing compound which liberates free, or elemental sulfur, at a temperature in a range of 140 °C to 190 °C. Such sulfur donors may be, for example, although are not limited to, polysulfide vulcanization accelerators and organosilane polysulfides with at least two connecting sulfur atoms in its polysulfide bridge. The amount of free sulfur source addition to the mixture can be controlled or manipulated as a matter of choice relatively independently from the addition of the aforesaid blocked mercaptosilane. Thus, for example, the independent addition of a sulfur source may be manipulated by the amount of addition thereof and by sequence of addition relative to addition of other ingredients to the rubber mixture.

[0041] Addition of an alkyl silane to the coupling agent system (blocked mercaptosilane plus additional free sulfur source and/or vulcanization accelerator) typically in a mole ratio of alkyl silane to blocked mercaptosilane in a range of 1/50 to 1/2 promotes an even better control of rubber composition processing and aging.

[0042] A rubber composition is prepared by a process which comprises the sequential steps of:

(A) thermomechanically mixing, in at least one preparatory mixing step, to a temperature of 140 °C to 200 °C, alternatively to 140 °C to 190 °C, for a total mixing time of 2 to 20, alternatively 4 to 15, minutes for such mixing step(s)

(i) 100 parts by weight of at least one sulfur vulcanizable rubber selected from conjugated diene homopolymers and copolymers, and copolymers of at least one conjugated diene and aromatic vinyl compound, (ii) 5 to 100, preferably 25 to 80, phr (parts per hundred rubber) of particulate filler, wherein preferably the filler contains 1 to 85 weight percent carbon black
(iii) 0.05 to 20 parts by weight filler of at least one blocked mercaptosilane;

(B) subsequently blending therewith, in a final thermomechanical mixing step at a temperature to 50 °C to 130 °C for a time sufficient to blend the rubber, preferably between 1 to 30 minutes, more preferably 1 to 3 minutes, at least one deblocking agent at about 0.05 to 20 parts by weight of the filler and a curing agent at 0 to 5 phr; and optionally

(C) curing said mixture at a temperature of 130 to 200 °C for about 5 to 60 minutes.

[0043] The process may also comprise the additional steps of preparing an assembly of a tire or sulfur vulcanizable rubber with a tread comprised of the rubber composition prepared according to this invention and vulcanizing the assembly at a temperature in a range of 130 °C to 200 °C.

[0044] Suitable organic polymers and fillers are well known in the art and are described in numerous texts, of which two examples include The Vanderbilt Rubber Handbook; R.F. Ohm, ed.; R.T. Vanderbilt Company, Inc., Norwalk, CT; 1990 and Manual For The Rubber Industry; T. Kempermann, S. Koch, J. Sumner, eds.; Bayer AG, Leverkusen, Germany; 1993. Representative examples of suitable polymers include solution styrene-butadiene rubber (SSBR), styrene-butadiene rubber (SBR), natural rubber (NR), polybutadiene (BR), ethylenepropylene co- and ter- polymers (EP, EP-DM), and acrylonitrile-butadiene rubber (NBR). The rubber composition is comprised of at least one diene-based elastomer, or rubber. Suitable conjugated dienes are isoprene and 1,3-butadiene and suitable vinyl aromatic compounds are styrene and alpha methyl styrene. Thus, the rubber is a sulfur curable rubber. Such diene based elastomer, or rubber, may be selected, for example, from at least one of cis-1,4-polyisoprene rubber (natural and/or synthetic), and preferably natural rubber), emulsion polymerization prepared styrene/butadiene copolymer rubber, organic solution polymerization prepared styrene/butadiene rubber, 3,4-polyisoprene rubber, isoprene/butadiene rubber, styrene/isoprene/butadiene terpolymer rubber, cis-1,4-polybutadiene, medium vinyl polybutadiene rubber (35-50 percent vinyl), high vinyl polybutadiene rubber (50-75 percent vinyl), styrene/isoprene copolymers, emulsion polymerization prepared styrene/butadiene/acrylonitrile terpolymer rubber and butadiene/acrylonitrile copolymer rubber. An emulsion polymerization derived styrene/butadiene (E-SBR) might be used having a relatively conventional styrene content of 20 to 28 percent bound styrene or, for some applications, an E-SBR having a medium to relatively high bound styrene content, namely, a bound styrene content of 30 to 45 percent. Emulsion polymerization prepared styrene/butadiene/acrylonitrile

terpolymer rubbers containing 2 to 40 weight percent bound acrylonitrile in the terpolymer are also contemplated as diene based rubbers for use in this invention.

[0045] The solution polymerization prepared SBR (S-SBR) typically has a bound styrene content in a range of 5 to 50, preferably 9 to 36, percent. Polybutadiene elastomer may be conveniently characterized, for example, by having at least a 90 weight percent cis-1,4-content.

[0046] Representative examples of suitable filler materials include metal oxides, such as silica (pyrogenic and precipitated), titanium dioxide, aluminosilicate and alumina, siliceous materials including clays and talc, and carbon black. Particulate, precipitated silica is also sometimes used for such purpose, particularly when the silica is used in connection with a silane. In some cases, a combination of silica and carbon black is utilized for reinforcing fillers for various rubber products, including treads for tires. Alumina can be used either alone or in combination with silica. The term "alumina" can be described herein as aluminum oxide, or Al_2O_3 . The fillers may be hydrated or in anhydrous form. Use of alumina in rubber compositions can be shown, for example, in US Patent No. 5,116,886 and EP 631 982.

[0047] The blocked mercaptosilane may be premixed, or pre-reacted, with the filler particles or added to the rubber mix during the rubber and filler processing, or mixing stage. If the silane and filler are added separately to the rubber mix during the rubber and filler mixing, or processing stage, it is considered that the blocked mercaptosilane then combines in situ with the filler.

[0048] The vulcanized rubber composition should contain a sufficient amount of filler to contribute a reasonably high modulus and high resistance to tear. The combined weight of the filler may be as low as about 5 to 100 phr, but is more preferably from 25 to 85 phr.

[0049] Precipitated silicas are preferred as the filler. The silica may be characterized by having a BET surface area, as measured using nitrogen gas, preferably in the range of 40 to 600, and more usually in a range of 50 to 300 m^2/g . The BET method of measuring surface area is described in the Journal of the American Chemical Society, Volume 60, page 304 (1930). The silica typically may also be characterized by having a dibutylphthalate (DBP) absorption value in a range of 100 to 350, and more usually 150 to 300. Further, the silica, as well as the aforesaid alumina and aluminosilicate, may be expected to have a CTAB surface area in a range of 100 to 220. The CTAB surface area is the external surface area as evaluated by cetyl trimethylammonium bromide with a pH of 9. The method is described in ASTM D 3849.

[0050] Mercury porosity surface area is the specific surface area determined by mercury porosimetry. For such technique, mercury is penetrated into the pores of the sample after a thermal treatment to remove volatiles. Set up conditions may be suitably described as using a 100 mg sample; removing volatiles during 2 hours at 105 °C and ambient atmospheric pressure; ambient to 2000 bars pressure measuring range. Such evaluation may be performed according to the method described in Winslow, Shapiro in ASTM bulletin, p.39 (1959) or according to DIN 66133. For such an evaluation, a CARLO-ERBA Porosimeter 2000 might be used. The average mercury porosity specific surface area for the silica should be in a range of 100 to 300 m^2/g .

[0051] A suitable pore size distribution for the silica, alumina and aluminosilicate according to such mercury porosity evaluation is considered herein to be:

five percent or less of its pores have a diameter of less than about 10 nm; 60 to 90 percent of its pores have a diameter of 10 to 100 nm; 10 to 30 percent of its pores have a diameter at 100 to 1,000 nm; and 5 to 20 percent of its pores have a diameter of greater than about 1,000 nm.

[0052] The silica might be expected to have an average ultimate particle size, for example, in the range of 0.01 to 0.05 μm as determined by the electron microscope, although the silica particles may be even smaller, or possibly larger, in size. Various commercially available silicas may be considered for use in this invention such as, from PPG Industries under the HI-SIL trademark with designations HI-SIL 210, 243, etc.; silicas available from Rhone-Poulenc, with, for example, designation of ZEOSIL 1165MP; silicas available from Degussa with, for example, designations VN2 and VN3, etc. and silicas commercially available from Huber having, for example, a designation of HUBERSIL 8745.

[0053] Where it is desired for the rubber composition, which contains both a siliceous filler such as silica, alumina and/or aluminosilicates and also carbon black reinforcing pigments, to be primarily reinforced with silica as the reinforcing pigment, it is often preferable that the weight ratio of such siliceous fillers to carbon black is at least 3/1 and preferably at least 10/1 and, thus, in a range of 3/1 to 30/1. The filler may be comprised of 15 to 95 weight percent precipitated silica, alumina and/or aluminosilicate and, correspondingly 5 to 85 weight percent carbon black, wherein the said carbon black has a CTAB value in a range of 80 to 150. Alternatively, the filler can be comprised of 60 to 95 weight percent of said silica, alumina and/or aluminosilicate and, correspondingly, 40 to 5 weight percent carbon black. The siliceous filler and carbon black may be pre-blended or blended together in the manufacture of the vulcanized rubber.

[0054] The rubber composition may be compounded by methods known in the rubber compounding art, such as mixing the various sulfur-vulcanizable constituent rubbers with various commonly used additive materials such as, for

example, curing aids, such as sulfur, activators, retarders and accelerators, processing additives, such as oils, resins including tackifying resins, silicas, plasticizers, fillers, pigments, fatty acid, zinc oxide, waxes, antioxidants and antiozonants, peptizing agents, and reinforcing materials such as, for example, carbon black. Depending on the intended use of the sulfur vulcanizable and sulfur vulcanized material (rubbers), the additives mentioned above are selected and commonly used in conventional amounts.

[0055] The vulcanization may be conducted in the presence of an additional sulfur vulcanizing agent. Examples of suitable sulfur vulcanizing agents include, for example elemental sulfur (free sulfur) or sulfur donating vulcanizing agents, for example, an amino disulfide, polymeric polysulfide or sulfur olefin adducts which are conventionally added in the final, productive, rubber composition mixing step. The sulfur vulcanizing agents (which are common in the art) are used, or added in the productive mixing stage, in an amount ranging from 0.4 to 3 phr, or even, in some circumstances, up to about 8 phr, with a range of from 1.5 to 2.5 phr, sometimes from 2 to 2.5 phr, being preferred.

[0056] Vulcanization accelerators, i.e., additional sulfur donors, may be used herein. It is appreciated that they may be, for example, of the type such as, for example, benzothiazole, alkyl thiuram disulfide, guanidine derivatives and thiocarbamates. Representative of such accelerators are, for example, but not limited to, mercapto benzothiazole, tetramethyl thiuram disulfide, benzothiazole disulfide, diphenylguanidine, zinc dithiocarbamate, alkylphenoldisulfide, zinc butyl xanthate, N-dicyclohexyl-2-benzothiazolesulfenamide, N-cyclohexyl-2-benzothiazolesulfenamide, N-oxydiethylenebenzothiazole-2-sulfenamide, N,N-diphenylthiourea, dithiocarbamylsulfenamide, N,N-diisopropylbenzothiazole-2-sulfenamide, zinc-2-mercaptotoluimidazole, dithiobis(N-methyl piperazine), dithiobis(N-beta-hydroxy ethyl piperazine) and dithiobis(dibenzyl amine). Other additional sulfur donors, may be, for example, thiuram and morpholine derivatives. Representative of such donors are, for example, but not limited to, dimorpholine disulfide, dimorpholine tetrasulfide, tetramethyl thiuram tetrasulfide, benzothiazyl-2,N-dithiomorpholide, thioplasts, dipentamethylenethiuram hexasulfide, and disulfidecaprolactam.

[0057] Accelerators are used to control the time and/or temperature required for vulcanization and to improve the properties of the vulcanizate. In one embodiment, a single accelerator system may be used, i.e., a primary accelerator. Conventionally and preferably, a primary accelerator(s) is used in total amounts ranging from 0.5 to 4, preferably 0.8 to 1.5, phr. Combinations of a primary and a secondary accelerator might be used with the secondary accelerator being used in smaller amounts (of 0.05 to 3 phr) in order to activate and to improve the properties of the vulcanizate. Delayed action accelerators may be used. Vulcanization retarders might also be used. Suitable types of accelerators are amines, disulfides, guanidines, thioureas, thiazoles, thiurams, sulfenamides, dithiocarbamates and xanthates. Preferably, the primary accelerator is a sulfenamide. If a second accelerator is used, the secondary accelerator is preferably a guanidine, dithiocarbamate or thiuram compound.

[0058] Typical amounts of tackifier resins, if used, comprise 0.5 to 10 phr, usually 1 to 5 phr. Typical amounts of processing aids comprise 1 to 50 phr. Such processing aids can include, for example, aromatic, naphthenic, and/or paraffinic processing oils. Typical amounts of antioxidants comprise 1 to 5 phr. Representative antioxidants may be, for example, diphenyl-p-phenylenediamine and others, such as, for example, those disclosed in the Vanderbilt Rubber Handbook (1978), pages 344-346. Typical amounts of antiozonants, comprise 1 to 5 phr. Typical amounts of fatty acids, if used, which can include stearic acid, comprise 0.5 to 3 phr. Typical amounts of zinc oxide comprise 2 to 5 phr. Typical amounts of waxes comprise 1 to 5 phr. Often microcrystalline waxes are used. Typical amounts of peptizers comprise 0.1 to 1 phr. Typical peptizers may be, for example, pentachlorothiophenol and dibenzamidodiphenyl disulfide.

[0059] The rubber composition of this invention can be used for various purposes. For example, it can be used for various tire compounds. Such tires can be built, shaped, molded and cured by various methods which are known and will be readily apparent to those having skill in such art.

[0060] All references cited herein are incorporated herein as they are relevant to the present invention.

[0061] The invention may be better understood by reference to the following examples in which the parts and percentages are by weight unless otherwise indicated.

EXAMPLES

EXAMPLE I Preparation of 3-(methyldiacetoxysilyl)-1-propyl thioacetate

[0062] A 5-liter flask was fitted with a 15-plate Oldershaw distilling column (28 mm plate diameter), to which was attached a condenser and distilling head capable of providing a controlled and adjustable reflux ratio. Heat was supplied to the flask using an electric heating mantle regulated by a controller coupled to an electronic temperature regulator. The vapor temperature in the head was monitored also. The system was maintained under an atmosphere of nitrogen. Control of the vacuum was enhanced via a bleeder valve inserted between the cold trap and the distillation head.

[0063] 738.1 grams of 3-(methyldimethoxysilyl)-1-propyl mercaptan and 1892.2 grams of acetic anhydride were added to the 5-liter flask. The mixture was heated with stirring until the first drops of liquid began to collect from the head, at which time the collection rate was adjusted to 1-2 drops per second. Heat was supplied to the flask at a sufficient

rate so as to maintain a reflux ratio of no less than 8:1, but not sufficient to cause column flooding. The collection temperature rapidly stabilized to 54 °C. The collection rate was increased and adjusted to maintain a collection temperature of not more than 55 °C until a total of 506 grams of a clear, colorless liquid had been collected. The distillate had an odor of methyl acetate, and was immiscible with and unresponsive toward aqueous sodium carbonate. Further distillation began with a collection at 54 °C, with a gradual tendency toward higher temperatures and slower collection rates until a steady collection in the range of 115-120 °C was maintained. 650 grams of a clear, colorless liquid were collected, which had an odor of acetic acid and methyl acetate, and demonstrated vigorous effervescence with aqueous sodium carbonate. After cooling, an additional 361 grams of acetic anhydride were added to the contents of the 5-liter flask, and the distillation was reinitiated. Collection eventually stabilized at 140 °C, yielding 493 grams of distillate. The temperature in the 5-liter flask had risen to 180 °C whereupon the heating was stopped. Both acetic acid and acetic anhydride could be detected in the distillate by odor. Its response with aqueous sodium carbonate was similar to the previous sample. A final sample of distillate was collected under vacuum. The vacuum was regulated and maintained at the level required to collect the distillate at a temperature near that of the cooling water used to remove heat from the condenser using the bleeder valve. The temperature in the 5-liter flask was limited to 150 °C during this procedure. The bleeder valve gradually was opened. An additional 428 grams of distillate collected. The final distillate had an odor of acetic anhydride. At this point, the temperature in the 5-liter flask was slowly increased, leading to the fractional distillation of the product at < 0.7 kPa. An initial 12-gram fraction was collected at <1 drop/second with a reflux ratio of >10:1. A second fraction of 950 grams of a clear, colorless liquid was collected at a substantially faster rate with a reflux ratio of >5:1. The distillation was terminated when the temperature of the 5-liter flask reached 180 °C, leaving a dark brown, viscous residue of 170 grams. The second fraction was product of 98.5 percent purity (GC); distilled yield, 83 percent.

EXAMPLE 2 Preparation of 3-(trimethoxysilyl)-1-propyl thioacetate

[0064] The apparatus used was identical to that of Example 1. 1074 grams of 3-(trimethoxysilyl)-1-propyl mercaptan and 561.4 grams of acetic anhydride were added to the 5-liter flask. The system was evacuated, followed by continuous application of vacuum using the bleeder valve in the nearly shut position. The temperature of the 5-liter flask was increased gradually to 120 °C, at which time condensate began collecting at <30 °C. The distillation was continued until nothing more collected with the 5-liter flask now at a temperature of 155 °C, at which time the heating was stopped, yielding 184 grams of a clear, colorless liquid with a distinct odor of methyl acetate. Its specific gravity of 0.898 combined with a negative response to aqueous sodium carbonate indicated that a substantial portion of methanol was probably present. The temperature of the 5-liter flask was now gradually raised to 195 °C, yielding an additional total of 266 grams of condensate. The distillation was continued with gradual heating of the 5-liter flask to 225 °C and the bleeder valve open. 379 grams of a clear, colorless liquid were collected at a maximum head temperature of 104 °C. GC analysis indicated that both the starting and product silanes were major components of the distillate, with small amounts of acetic acid detectable by odor.

[0065] The contents of the 5-liter flask were emptied into and stored in a 32-oz. (947 ml) bottle under nitrogen. The 5-liter flask was charged with the distillate, which was redistilled with the bleeder valve wide open. A large first fraction contained mostly the starting blocked mercaptosilane. A second, clear and colorless 75 gram fraction was collected at 70 °C. This fraction was product of >90% purity (GC); distilled yield, 6 percent. The product also contained derivative containing methoxy-Si and acetoxy-Si groups, and SiOSi crosslinks.

EXAMPLE 3 Preparation of 3-(trimethoxysilyl)-1-propyl thioacetate derivative containing acetoxy-Si groups and SiOSi crosslinks

[0066] The apparatus used was identical to that of Example 1. 1775 grams of 3-(trimethoxysilyl)-1-propyl mercaptan were added to the 5-liter flask. A total of 4719 grams of acetic anhydride were set aside for reaction with the mercaptosilane, of which 1002 grams were added to the 5-liter flask along with the mercaptosilane. The heat flow to the 5-liter flask was increased gradually until a steady collection of distillate was established at a head temperature of 54 °C. A total of 840 grams of distillate were collected, which was found to contain methyl acetate, acetic acid, and methanol in a 100/2/2.7 molar ratio by NMR analysis. An additional 2015 grams of acetic anhydride were added to the cooled 5-liter flask, and the distillation resumed, yielding an additional 923 grams of distillate. The procedure was then repeated a third time with a 701 grams addition of acetic anhydride, yielding 834 grams of distillate. The application of vacuum to the head was now begun. The vacuum was regulated and maintained at the level required to collect the distillate at a temperature near that of the cooling water used to remove heat from the condenser via the bleeder valve. The temperature in the 5-liter flask was limited to 170 °C during this procedure. The bleeder valve was opened gradually as the collection rate began to diminish. An additional 896 grams of distillate collected, whereupon any remaining liquids in the column and head evaporated. GC analysis of the final distillate indicated that essentially nothing less

volatile than acetic anhydride had distilled over. The contents of the flask cooled to a viscous, dark brown oil, which was stored under nitrogen.

EXAMPLE 5 - Preparation of 3-(propionylthio)-1-propyltrimethoxysilane

[0067] 816 grams of 3-mercapto-1-propyltrimethoxysilane, 871 grams of 25 weight percent methanolic solution of sodium methoxide and 1724 grams of toluene were charged to a 5-liter flask under an atmosphere of nitrogen. The stirred mixture developed a pinkish color. Methanol was removed from the flask by distilling off a methanol-toluene azeotrope, during which time the contents of the flask turned colorless. The appearance of a strong density current in the distillate which coincided with an increase in distillation head temperature from 63 °C to 108 °C signaled the point at which methanol removal from the flask was complete. With continued stirring, the contents of the flask were allowed to cool and were placed in an ice-water bath. 361 grams of propionyl chloride were added to the flask drop-wise and/or in small portions with continued stirring in an ice-water bath until the reaction was complete. Aliquots of the stirred mixture were taken periodically and placed onto pH paper. An alkaline reading indicated the completion of the reaction. The final mixture was a white suspension of NaCl in a toluene solution of the product. This mixture was filtered and the solvent was removed from the filtrate to yield a light brown product. Gas chromatography indicated 5 percent 3-mercapto-1-propyltrimethoxysilane, 25 percent of 3-(methylthio)-1-propyltrimethoxysilane, 70 percent of 3-(propionylthio)-2-propyltrimethoxysilane (product). Rash distillation from 1 to 2 grams of powdered sodium methoxide yielded a colorless product. The sodium methoxide was added to insure that any remaining acidity was neutralized. Further optional fractional distillation yielded a product in excess of 98 percent purity by GC.

EXAMPLE 6 - Preparation of 3-(propionylthio)-1-propyltrimethoxysilane

[0068] 1035 grams of 3-mercapto-1-propyltrimethoxysilane, 1096 grams of a 25 weight percent methanolic solution of sodium methoxide, and 1764 grams of toluene were charged to a 5-liter flask under an atmosphere of nitrogen. The stirred mixture developed a pinkish color. The flask was placed into a water bath at 64 °C. Methanol was removed from the flask by distilling off a methanol-toluene azeotrope under a partial vacuum. The vacuum was kept such that the temperature in the distillation head was maintained at 30 to 35 °C during which time 1500 ml of distillate, consisting of a toluene-methanol azeotrope, was collected. During this time the contents of the flask turned colorless. An additional 429 grams of toluene was added and the distillation resumed. The appearance of a strong density current in the distillate which coincided with an increase in distillation head temperature from 35 to 55 °C and the appearance of a changing liquid surface tension in the condenser signaled the point at which methanol removal from the flask was complete. The contents of the flask had become a viscous fluid. With continued stirring, the contents of the flask were allowed to cool. The flask was placed in an ice-water bath, resulting in what appeared to be a thick paste. 457 grams of propionyl chloride was added to the flask drop-wise and/or in small portions with continued stirring in an ice-water bath until the reaction was complete. Aliquots of the stirred mixture were taken periodically. An alkaline reading indicated the completion of the reaction. The final mixture was a white suspension of NaCl in a toluene solution of the product. This mixture was filtered and the solvent was removed from the filtrate to yield a nearly colorless product. Gas chromatography indicated (by weight) 3 percent of 3-mercapto-1-propyltrimethoxysilane, 1 percent of 3-(methylthio)-1-propyltrimethoxysilane, and 96 percent of 3-(propionylthio)-2-propyltrimethoxysilane (product). Flash distillation from 1 to 2 grams of powdered sodium methoxide yielded a colorless product. The sodium methoxide was added to ensure that any remaining acidity was neutralized. Further optional fractional distillation yielded a product in excess of 98 percent purity by GC.

EXAMPLE 7 Preparation of 3-(benzoylthio)-1-propyltriethoxysilane

[0069] 763 grams of 3-mercapto-1-propyltriethoxysilane and 1013 grams of a 21 weight percent ethanolic solution of sodium ethoxide were charged to a 5-liter flask under an atmosphere of nitrogen. 870 grams of ethanol were distilled from this mixture at a maximum temperature of 45 °C at 48 kPa. 1550 grams of toluene were added to the contents of the flask under nitrogen. The remaining ethanol was removed from the flask by distilling off an ethanol-toluene azeotrope under a maximum absolute pressure of 48 kPa at a maximum temperature of 60 °C. The vacuum was kept such that the temperature in the distillation head was maintained at 30 to 40 °C. The appearance of a strong density current in the distillate which coincided with an increase in distillation head temperature from 35 to about 60 °C and the appearance of a changing liquid surface tension in the condenser signaled the point at which ethanol removal from the flask was complete. At the end of this procedure the contents of the flask had become a clear, orange liquid.

[0070] With continued stirring, the contents of the flask were allowed to cool to ambient temperature. 418 grams of benzoyl chloride was added to the flask drop-wise and/or in small portions at a sufficiently slow rate to prevent the temperature from rising above 50 °C. At the completion of the benzoyl chloride addition, stirring was continued for an

additional day. The stirring was initially sufficiently vigorous to break up any chunks and inhomogeneities in the mixture. The resulting final mixture was a white suspension of NaCl in a toluene solution of the product. This mixture was filtered and the solvent was removed from the filtrate to yield a light yellow-brown product which gave an acidic response to pH paper. Sufficient powdered sodium ethoxide was stirred into the product to neutralize all of the acidity. Flash distillation at <0.7 kPa yielded a light pink product containing about 10 percent by gas chromatography each of ethyl benzoate and 1-sila-2-thia-1,1-diethoxycyclopentane, which formed because of base catalyzed decomposition during the distillation. A second flash distillation was performed in which the first 30 percent of the product was removed as a forecut. No base or acid was present. The second fraction was a product of light pink color in excess of 98 percent purity by GC.

EXAMPLE 8 Preparation of 2-(acetylthio)-1-ethyltriethoxysilane

[0071] 2513 grams of vinyltriethoxysilane was added to a 5-liter flask and brought to reflux with stirring. A 25 ml forecut was distilled off to remove volatile impurities. The heating was stopped and a first, 335 gram portion of a total of two portions of 1005 grams of thiolacetic acid was added over a period of several minutes at a rate to maintain a smooth reflux. Heat was supplied toward the end of the addition, as necessary, to maintain the reflux. 0.8 grams of di-*t*-butyl peroxide was added down the condensers, resulting in an immediate reaction as evidenced by a reflux rate acceleration. Power to the heating mantle was cut. During the reflux, the temperature rose to near 160 °C within several minutes, whereupon the reflux subsided and the light yellow contents of the pot began to cool.

[0072] When the contents of the pot had reached 150 °C, an additional 670 grams of thiolacetic acid was added in a manner similar to the first addition. 20 ml. of forecut were collected, and 1.6 grams of di-*t*-butyl peroxide was again added. A slight increase in reflux rate was observed within several minutes. After 10 to 15 minutes, the pot reached a maximum temperature of 155 °C and subsequently began to cool. At 150 °C the temperature was maintained by the heating mantle for one hour. The pot was allowed to cool under nitrogen. Gas chromatography analysis indicated (by weight) 2 percent thiolacetic acid, 16 percent vinyltriethoxysilane, 5 percent; 1-(acetylthio)-1-ethyltriethoxysilane (alpha adduct), 68 percent 2-(acetylthio)-1-ethyltriethoxysilane (beta adduct product), and 9 percent balance (mainly heavies).

EXAMPLE 9 - Preparation of 3-(octanoylthio)-1-propyltriethoxysilane

[0073] Into a 12 liter, 3 necked round bottom flask equipped with mechanical stirrer, addition funnel, thermocouple, heating mantle, N₂ inlet and temperature controller was charged 1,021 grams of 3-mercaptopropyltriethoxysilane (SILQUEST® A-1891 silane from OSI Specialties, Inc., a subsidiary of Witco Corp. of Greenwich, CT), and 433 grams of triethylamine and 3,000 ml hexane. The solution was cooled in an ice bath, and 693 grams of octanoyl chloride was added over a two hour period via the addition funnel. After addition of the acid chloride was complete, the mixture was filtered two times, first through a 0.1 µm filter and then through a 0.01 µm filter, using a pressure filter, to remove the salt. The solvent was removed under vacuum. The remaining yellow liquid was vacuum distilled to yield 1,349 grams of octanoylthiopropyltriethoxysilane as a clear, very light yellow liquid. The yield was 87 percent.

EXAMPLE 10 - Preparation of 3-(acetylthio)-1-propyltriethoxysilane

[0074] This example illustrates the preparation of a thiocarboxylate alkoxysilane from a salt of a thiolcarboxylic acid using as a solvent the alcohol corresponding to the silane alkoxy group. Into a 250 ml, 3 neck round bottomed flask equipped with magnetic stir bar, temperature probe/controller, heating mantle, addition funnel, condensor, and N₂ inlet was charged 63 grams of a 21 weight percent sodium ethoxide in ethanol. 15 grams of thiolacetic acid was added slowly, keeping the temperature below 65 °C. The solution was allowed to cool to room temperature, and 48 grams of chloropropyltriethoxysilane was added via the addition funnel. After addition was complete, the solution was heated to 70 °C for 24 hours whereupon a white solid formed. Analysis of the solution by gas chromatography showed a 78 percent yield of acetylthiopropyltriethoxysilane.

EXAMPLE 11 - Preparation of acetylthiomethyltriethoxysilane

[0075] This example illustrates the preparation of a thiocarboxylate alkoxysilane from a salt of a thiolcarboxylic acid using as a nonprotic solvent. 88 grams of powdered sodium ethoxide and 600 ml diglyme were charged into a 1 liter, 3 neck round bottomed flask equipped with magnetic stir bar, temperature probe/controller, heating mantle, addition funnel, condenser, N₂ inlet, and ice water bath. The solution was cooled to 8 °C and 105 grams of thiolacetic acid was added slowly via the addition funnel, keeping the temperature below 60 °C. The solution was allowed to cool to 35 °C, and 250 grams of chloromethyltriethoxysilane was added via the addition funnel. After addition was complete, the solution was heated to 70 °C, where a brief exotherm to 120 °C was observed. The solution was heated at 70 °C for

an additional 3 hours. A white solid formed which was filtered first through a 0.1 μm pressure filter and then a 0.01 μm filter to give a clear, black solution. The solvent was removed under reduced pressure, and the remaining liquid vacuum distilled to yield 163 grams of a clear and colorless liquid, a 55 percent yield.

EXAMPLE 12 The Use of Silanes of Ex. 1-4 in Low Rolling Resistant Tire Tread Formulation

[0076] A model low rolling resistance passenger tire tread formulation as described in Table 1 and a mix procedure, were used to evaluate representative examples of the silanes of the present invention. The silane in Example 1 was mixed as follows in a "B" BANBURY® (Farrell Corp.) mixer with a 103 cu. in. (1690 cc) chamber volume. The mixing of the rubber masterbatch was done in two steps. The mixer was turned on with the mixer at 120 rpm and the cooling water on full. The rubber polymers were added to the mixer and ram down mixed for 30 seconds. Half of the silica and all of the silane with approximately 35-40 grams of this portion of silica in an ethylvinyl acetate (EVA) bag were added and ram down mixed for 30 seconds. The remaining silica and the oil in an EVA bag were next added and ram down mixed for 30 seconds. The mixer throat was thrice dusted down and the mixture ram down mixed for 15 seconds each time. The mixer's mixing speed was increased to 160 or 240 rpm, as required to raise the temperature of the rubber masterbatch to between 160 and 165 °C in approximately 1 minute. The masterbatch was dumped (removed from the mixer), a sheet was formed on a roll mill set at about 50 to 60 °C, and then allowed to cool to ambient temperature.

[0077] The rubber masterbatch was added to the mixer with the mixer at 120 rpm and cooling water turned on full and ram down mixed for 30 seconds. The remainder of the ingredients were added and ram down mixed for 30 seconds. The mixer throat was dusted down, the mixer speed increased to 160 or 240 rpm so that the contents reached a temperature between 160 and 165 °C in approximately 2 minutes. The rubber masterbatch was mixed for 8 minutes and the speed of the BANBURY mixer was adjusted to maintain the temperature between 160 and 165 °C. The masterbatch was dumped (removed from the mixer), a sheet was formed on a roll mill set at about 50 to 60 °C, and then allowed to cool to ambient temperature.

[0078] The rubber masterbatch and the curatives were mixed on a 6 in. x 13 in. (15 cm X 33 cm) two roll mill that was heated to between 50 and 60 °C. The sulfur and accelerators were added to the rubber masterbatch and thoroughly mixed on the roll mill and allowed to form a sheet. The sheet was cooled to ambient conditions for 24 hours before it was cured. The rheological properties were measured on a Monsanto R-100 Oscillating Disk Rheometer and a Monsanto M1400 Mooney Viscometer. The specimens for measuring the mechanical properties were cut from 6 mm plaques cured for 35 minutes at 160 °C or from 2 mm plaques cured for 25 minutes at 160 °C.

[0079] Silane from Examples 2-4 were compounded into the tire tread formulation according to the above procedure. The performance of the silanes prepared in Examples 1-4 was compared to the performance of no silane coupling agent (Silane α), two silanes, one of which is practiced in the prior art, bis-(3-triethoxysilyl-1-propyl)tetrakisulfide (TESPT, Silane β), the other 3-triethoxysilyl-1-propylmercaptan (TESPM, Silane γ) which is the product resulting from the loss of a carboxyl blocking group from a representative example of the silanes of the present invention. The results of this procedure are tabulated below in Table 2.

Table 1 -

Model Low Rolling Resistance Tread Formulation	
PHR	Ingredient
75	SSBR (12% styrene, 46% vinyl, T_g : 42°C)
25	BR (98% cis, T_g : 104°C)
80	Silica (150-190 m ² /gm, ZEOSIL 1165MP, Rhone-Poulenc)
32.5	Aromatic process oil (high viscosity, Sundex 8125, Sun)
2.5	Zinc oxide (KADOX 720C, Zinc Corp)
1	Stearic acid (INDUSTRENE, Witco)
2	6PPD antiozonant (SANTOFLEX 6PPD, Flexsys)
1.5	Microcrystalline wax (M-4067, Schumann)
3	N330 carbon black (Engineered Carbons)
1.4	Sulfur (#104, Sunbelt)
1.7	CBS accelerator (SANTOCURE, Flexsys)
2	DPG accelerator (PERKACIT DPG-C, Flexsys)

[0080] The following tests were conducted with the following methods (in all examples): Mooney Scorch @ 135 °C (ASTM Procedure D1646); Mooney Viscosity @ 100 °C (ASTM Procedure D1646); Oscillating Disc Rheometer (ODR)

EP 0 958 298 B1

@ 149 °C, 1° arc, (ASTM Procedure D2084); Physical Properties, cured t90 @ 149 °C (ASTM Procedures D412 and D224) (G' and G'' in dynes/cm²); DIN Abrasion, mm³ (DIN Procedure 53516); and Heat Build (ASTM Procedure D623).

Table 2 -

Performance of Representative Silanes in a Model Low Rolling Resistance								
Passenger Tire Tread Formulation								
Silane Amount	α ---	β 7.4	Ex. 4 7.4	Ex. 3 7.4	Ex. 1 7.4	Ex. 2 8.3	γ 3.18	γ 6.35
Mooney Viscosity at 100 °C								
ML1+4	130	67	65	58	73	63	74	121
Mooney Scorch at 135 °C								
MS1+, t ₃ , minutes	9.5	6.7	4.3	6.3	2.2	6.3	6.3	2.8
MS1+,t ₁₈ ,	11.0	10.1	5.9	7.8	3.2	7.7	8.4	3.7
ODR @ 149°C,1° Arc, 30 minute timer								
M _L , dN-M	26.9	8.5	8.5	7.2	9.3	7.8	11.5	14.8
M _H , dN-M	44.5	30.8	31.0	31.4	34.8	30.5	27.8	33.9
t _{SI} , minutes	5.4	4.8	2.5	3.8	1.6	3.8	3.8	2.0
t90, minutes	10.5	17.8	8.0	8.0	8.1	7.5	15.3	15.0
Physical Properties, cured t90 @ 149°C								
Hardness, Shore A	66	57	59	60	62	60	52	scorched
Elongation, %	900	400	540	520	490	450	360	not cured
100% Mod., kg/cm ²	10.5	19.0	19.0	18.3	22.5	23.2	15.5	
200% Mod., kg/cm ²	15.5	56.9	49.2	46.4	59.8	66.1	45.0	
300% Mod., kg/cm ²	24.6	128.0	101.2	96.3	116.0	129.4	104.8	
Tensile, kg/cm ²	137.1	208.1	234.8	218.0	237.6	222.9	139.2	
Dynamic Properties @ 0.15% strain, 10Hz, torsion mode (2nd sweep)								
G' @ 0°C, x 10 ⁷	26.8	5.92	9.22	9.42	1.26	6.41	3.17	
G' @ 60°C, x 10 ⁷	12.7	2.76	4.26	3.89	5.36	3.02	1.75	
G" @ 0°C, x 10 ⁷	2.87	1.26	1.81	1.84	2.14	1.3	5.69	
G" @ 60°C, x 10 ⁶	11.2	2.48	4.00	3.85	4.94	2.71	2.13	
Tan delta @ 0°C	0.1070	0.2124	0.1968	0.1952	0.169	0.202	0.202	
Tan delta @ 60°C	0.0876	0.09	0.0939	0.0988	0.092	0.089	0.121	
Ratio, 0°C/60°C	1.22	2.36	2.10	1.98	1.84	2.25	1.67	
Heat Build-up, 100 °C ambient, 18.5% compression, 143 psi (99KPa) load, 25 minutes								
Delta T, °C	66	13	22	19	18		17	
Set, %	***	6.3	10.9	8.8	8.0		6.9	

***delaminated in 9

EXAMPLE 13 - The Use of Silane of Example 1 in Low Rolling Resistance Tire Formulation Activated by Varying Levels of DPG

[0081] The model low rolling resistance passenger tire tread formulation and mixing procedure of Example 12 were used to evaluate the silane of Example 1 at three levels of N,N'-diphenylguanidine (DPG). The results are tabulated below in Table 3.

Table 3.

The Effect of DPG on the Compounding and Curing of a Model Low Rolling			
Resistance Passenger Tire Tread Formulation			
Run phr DPG	A 2.00	B 0.5	C 1.25
Mooney viscosity @ 100 °C			
ML 1+4	75	---	---
Mooney scorch @ 135 °C			
M _v	41	---	---
MS 1+, t ₃ , minutes	2.5	15.3	6.2
MS 1+, t ₁₈ , minutes	3.6	24.1	8.3
ODR @ 149°C, 1° arc, 30 minute timer			
M _L , dN-M	9.8	9.4	8.6
M _H , dN-M	35.7	28.8	33.4
t ₉ , minutes	1.8	8.0	3.4
t ₉₀ , minutes	8.0	22.5	11.8
Physical properties, cured t ₉₀ @ 149 °C			
Hardness, Shore A	63	59	62
Elongation, %	550	620	560
100% Modulus, kg/cm ²	21.1	19.0	22.5
200% Modulus, kg/cm ²	55.5	42.9	55.5
300% Modulus, kg/cm ²	106.9	80.9	106.2
Tensile, kg/cm ²	236	209.5	234.1
DIN Abrasion, mm ³	85	69	72
Dynamic properties @ 10Hz, 0.15% strain, torsion mode			
G' @ 0°C, X10 ⁷	14.8	14.1	12.6
G' @ 60°C, X10 ⁷	6.23	5.97	5.64
G'' @ 0°C, X10 ⁷	23.0	26.4	22.1
G'' @ 60°C, X10 ⁶	6.55	7.30	6.01
Tan delta @ 0°C	0.1551	0.1872	0.1753
Tan delta @ 60°C	0.1053	0.1189	0.1035
Ratio 0°C/60°C	1.47	1.57	1.69

EXAMPLE 14 - Shoe Sole Compound Compositions

[0082] Formulation: 60 Budene 1207 BR, 40 SMR5L NR, 45 ZEOSIL 1165MP Silica, 5 CALSOL 5550 Process Oil, 3 CARBOWAX 3350 PEG, 5 KADOX 720C Zinc Oxide, 1 INDUSTRENE R Stearic Acid, 1 BHT Antioxidant, 1 SUNO-LITE 240 Wax, 1.9 Rubbermakers Sulfur 104, 1.3 MBTS, 0.5 MBT, 0.2 TMTM, Silane - SILQUEST A-1289 silane (TESPT) or acetylthiopropyltriethoxysilane (Acetyl). The amounts of each are in phr. The term "Add Sulfur" or "Add S" means that additional sulfur was added to make the amount of sulfur in the Acetyl equivalent to the amount of sulfur delivered by TESPT. The results are set forth in Table 4 below.

Table 4

SILANE	NONE	TESPT	TESPT	Acetyl	Acetyl	Acetyl	Acetyl
Add Sulfur	---	2	4	2	X	---	X
	---				2	4	4

Table 4 (continued)

SILANE	NONE	TESPT	TESPT	Acetyl	Acetyl	Acetyl	Acetyl
Mooney Scorch @ 135 °C							
MV	51	42	40	36		33	
MS1+, t ₃ , minutes	5.0	4.3	4.3	6.9		7.4	
MS1+, t ₁₈ , minutes	5.8	5.3	5.3	8.2		8.8	
Mooney Viscosity @ 100 °C							
ML1+4	96	78	76	74		71	
ODR @ 149 °C. 1° arc, 12 minute timer							
M _L , dN-m	19.7	14.9	14.0	12.2	11.5	10.4	10.2
M _H , dN-m	59.7	57.4	54.2	52.0	52.8	49.3	49.8
t _{s1} , minutes	3.5	2.8	2.8	4.3	3.8	4.7	4.4
t ₉₀ , minutes	5.7	5.6	5.9	7.5	7.1	8.2	8.2
Physical Properties, cured t₉₀ @ 149 °C							
Hardness, Shore A	67	67	66	66	66	66	66
Elongation, %	630	570	570	540	440	500	460
100% Modulus, kg/cm ²	19.7	23.9	25.3	26.7	26.7	26.7	27.4
200% Modulus, kg/cm ²	36.6	50.6	54.1	56.2	59.1	55.5	59.8
300% Modulus, kg/cm ²	58.3	86.5	91.4	97.7	103.3	96.3	105.5
Tensile, Kg/cm ²	187.0	204.6	222.2	201.1	174.4	189.8	189.1
DIN Abrasion, mm ³	86	75	67	74	71	65	73
Akron Abrasion, mm ³	0.46	0.48	0.35	0.39	0.41	0.45	0.44

EXAMPLE 15 - Low Rolling Resistance Tire Formulations

[0083] The- following silanes were tested in low rolling resistance tire formulations: TESPT (A); TESPM (B); 3-acetylthio-1-propyltrimethoxysilane (C); 3-acetylthio-1-propyltriethoxysilane (D); 3-octanoylthio-1-propyltriethoxysilane (E); 3-palmitoylthio-1-propyltriethoxysilane (F); 3-ethylhexanoyl-1-propyltriethoxysilane (G); 3-propionylthio-1-propyltrimethoxysilane (H); 3-benzoylthio-1-propyltriethoxysilane (I); acetylthiomethyltriethoxysilane (J), acetylthioethyltrimethoxysilane (K), acetylthioethyltriethoxysilane (L), acetothioethylmethyldimethoxysilane (M), acetylthiooctyltrimethoxysilane (N), acetylthiooctyltriethoxysilane (O), acetylthiocyclohexylethyltrimethoxysilane (P), and acetothionorbornylethyltrimethoxysilane (Q). The formulation was (amounts in phr) 75 SOLFLEX 1216 SSB, 25 Budene 1207 BR, 80 ZEOSIL 1165MP silica, 32.5 SUNDEX 3125 process oil, 2.5 KADOX 720C zinc oxide, 1.0 INDUSTRENE R stearic acid, 2.0 SANTOFLEX 13 antiozonant, 1.5 M4067 microwax, 3.0 N330 carbon black, 1.4 Rubbermakers sulfur 104, 1.7 CBS, 2.0 DPG, Silane as shown.

Table 5

Stilane	A	B	C	C	D	D	E	E	F	F	G	H	H
Add S													
Amount	7.0	6.36	6.36	6.33	6.33	7.45	7.45	9.69	9.69	12.67	12.67	9.62	6.7
Mooney Viscosity @ 100 °C													
MI, I+4	94	74	74	72	--	62	--	55	--	50	--	52	66
Mooney Scorch @ 135 °C													
MS1+, t ₉₀ , minutes	6.2	9.9	9.0	6.9	7.5	6.3	6.3	10.4	9.6	13.0	11.9	16.8	8.3
MS1+, t ₉₀ , minutes	8.9	12.6	11.5	9.3	10.2	7.6	7.8	11.7	11.7	14.6	13.9	19.0	9.6
ODR @ 149 °C, 1° arc, 30 minute timer													
M _L , dN-m	9.6	8.1	8.1	8.7	8.5	7.9	7.7	6.7	6.8	5.7	5.7	5.5	8.2
M ₁₀ , dN-m	31.8	29.5	34.5	32.0	36.7	29.9	33.9	27.8	32.3	26.8	30.7	31.6	30.1
t ₉₀ , minutes	4.5	5.4	5.1	4.1	4.5	3.6	3.5	5.6	5.5	7.0	6.8	9.1	4.5
t ₉₀ , minutes	17.6	10.4	14.1	11	11.5	8.0	7.5	11.3	9.8	12.3	11.0	14.1	9.5
Physical Properties cured 190 @ 149°C													
Hardness, Shore A	57	58	60	64	66	59	60	53	55	51	54	56	58
Elongation, %	420	560	440	660	570	630	540	600	490	740	610	600	540
100% Modulus, kg/cm ²	20.4	16.9	22.5	17.6	22.5	15.5	19.0	14.1	17.6	12.7	15.5	15.5	16.2
200% Modulus, kg/cm ²	58.4	40.1	59.8	38.7	54.8	34.5	49.9	34.5	49.2	27.4	36.6	35.9	38.0
300% Modulus, kg/cm ²	123.7	84.4	123.0	73.8	105.5	71.7	104.1	77.3	105.5	55.5	71.0	69.6	80.2
Tensile, kg/cm ²	210.9	210.3	211.6	225.0	250.3	223.6	236.2	227.8	213.7	205.3	186.3	175.8	234.1
DIN Abrasion mm ³	71	69	76	114	97	131	90	99	92	--	--	157	127
Heat Build-up @ 100 °C, 17.5% compression, 99 KPa static, 25 minute run													
Delta T, °C	13.3	18.9	13.3	32.2	18.3	21.1	13.3	12.2	8.9	--	--	10.5	18.9
Permanent set, %	6.2	10.5	6.3	25.3	12.3	14.5	9.8	5.0	4.6	--	--	7.0	11.0
Dynamic Properties @ 0.15% strain, 10Hz, torsion mode													
G' @ 0°C, dyn/cm ² X 10 ⁷	6.73	12.8	12.4	20.1	16.6	12.8	10.4	4.80	4.62	6.40	5.93	9.29	10.1
G' @ 60°C, dyn/cm ² X 10 ⁷	3.00	5.13	5.15	8.73	2.67	5.10	1.93	2.44	0.82	2.42	1.13	1.88	4.18
G'' @ 0°C, dyn/cm ² X 10 ⁷	1.46	2.44	2.43	3.39	7.06	2.47	4.05	0.98	2.00	1.27	2.17	3.64	2.07
G'' @ 60°C, dyn/cm ² X 10 ⁶	2.93	5.23	4.47	8.35	5.33	5.79	3.21	2.14	1.27	2.34	1.23	3.08	4.62
Tan delta @ 0°C	0.216	0.191	0.196	0.168	0.161	0.192	0.185	0.205	0.177	0.199	0.191	0.202	0.205
Tan delta @ 60°C	0.098	0.102	0.087	0.096	0.075	0.114	0.079	0.088	0.064	0.097	0.057	0.085	0.110
Ratio, 0°C/60°C	2.22	1.88	2.26	1.75	2.15	1.68	2.34	2.33	2.77	2.05	3.35	2.39	1.86

Table 5 (cont.)

Add S	I	J	K	K	L	L	M	M	N	N	O	O	P	Q
Silane				X	X	X	X	X	X	X	X	X	X	X
Amount	9.1	6.7	5.96	5.96	7.08	7.08	5.54	5.54	8.19	8.19	9.31	9.31	8.14	8.46
Mooney Viscosity @ 100 °C														
MLI+4	55	69	73	--	63	--	71	--	65	--	54	--	52	63
Mooney Scorch @ 135 °C														
MSI+, t ₁ , minutes	11.5	2.5	4.6	4.3	4.5	4.6	4.7	4.9	9.4	8.9	11.5	11.2	8.9	9.5
MSI+, t ₁₀ , minutes	13.5	3.5	5.6	5.6	5.3	5.6	5.8	6.1	12.6	11.9	13.2	13.3	10.7	11.3
ODR @ 149 °C, 1° arc, 30 minute timer														
M ₁ , dN-m	6.2	8.8	9.5	9.0	6.8	7.7	9.4	9.3	8.6	8.5	6.7	6.6	7.0	6.8
M ₁₀ , dN-m	35.0	32.5	29.8	34.1	27.5	31.3	33.9	38.1	34.5	37.0	30.7	34.7	38.4	37.6
t ₁₀ , minutes	6.3	1.9	2.8	2.8	2.8	2.8	3.0	2.9	5.3	4.8	5.6	5.9	4.8	5.5
t ₉₀ , minutes	11.3	17.0	16.8	15.3	11.3	9.5	13.5	11.8	12.0	11.9	10.3	10.9	10.5	10.0
Physical Properties cured t90 @ 149 °C														
Hardness, Shore A	62	61	61	65	56	58	66	65	61	63	57	58	67	66
Elongation, %	560	440	500	470	580	560	530	530	640	590	580	530	640	580
100% Modulus, kg/cm ²	19.0	19.0	19.0	20.4	14.8	17.6	21.1	22.5	17.6	21.1	15.5	18.3	21.1	22.5
200% Modulus, kg/cm ²	47.8	51.3	43.6	51.3	33.7	42.9	47.1	55.5	41.5	52.7	34.5	46.4	48.5	52.7
300% Modulus, kg/cm ²	107.5	109.0	84.4	105.5	69.6	91.4	87.9	105.5	80.9	100.5	71.7	92.8	86.5	94.2
Tensile, kg/cm ²	210.9	198.2	184.9	208.1	199.0	234.8	196.9	225.7	227.1	241.9	203.2	208.1	219.4	210.9
DIN Abrasion, mm ³	133	88	113	103	133	96	101	96	100	94	113	97	141	132
Heat Build-up @ 100 °C, 17.5% compression, 99 KPa static load, 25 minute run														
Delta T, °C	12.8	15.6	21.7	16.1	28.9	16.7	25.0	16.7	21.1	15.6	14.4	10.0	17.2	15.0
Permanent set, %	7.9	10.8	13.7	8.7	23.2	11.2	17.3	9.2	16.8	12.6	11.0	7.5	12.7	10.8
Dynamic Properties @ 0.15% strain, 10Hz, torsion mode														
G' @ 0°C, dyn/cm ² x 10 ⁷	17.9	10.8	18.2	16.1	10.1	8.94	27.7	22.2	14.9	12.4	10.2	8.10	27.6	23.8
G' @ 60°C, dyn/cm ² x 10 ⁷	2.99	2.16	6.60	2.70	4.30	1.73	9.54	3.39	5.72	2.33	4.25	1.55	3.72	3.59
G'' @ 0°C, dyn/cm ² x 10 ⁷	6.38	3.92	3.27	5.86	2.12	3.65	4.33	7.79	2.93	4.85	2.06	2.80	10.8	9.04
G'' @ 60°C, dyn/cm ² x 10 ⁶	6.83	4.87	9.41	5.92	5.32	2.92	14.0	9.17	5.75	3.62	4.06	2.44	12.4	9.61
Tan delta @ 0 °C	0.167	0.201	0.180	0.167	0.210	0.193	0.156	0.153	0.197	0.187	0.202	0.192	0.135	0.151
Tan delta @ 60 °C	0.107	0.124	0.143	0.101	0.124	0.080	0.147	0.118	0.101	0.075	0.096	0.087	0.115	0.106
Ratio, 0 °C/60 °C	1.56	1.67	1.26	1.65	1.69	2.41	1.06	1.30	1.95	2.49	2.10	2.21	1.18	1.42

Claims

1. A process for the manufacture of a filled rubber comprising:

- mixing a rubber, a blocked mercaptosilane and inorganic filler;
- mixing into the mixture of step (a) a deblocking agent to the mixture to deblock the mercaptosilane and a curing agent; and
- allowing the mixture to cure.

2. A process according to claim 1 wherein mercaptosilane is selected from the group consisting of:



and



wherein

Y is a polyvalent species $(\text{Q})_z\text{A}(=\text{E})$, each wherein the atom (A) attached to the unsaturated heteroatom (E) is attached to the sulfur, which in turn is linked via a group G to the silicon atom;

each R is chosen independently from straight, cyclic or branched alkyl, alkenyl groups, aryl groups, and aralkyl groups, with each R containing from 1 to 18 carbon atoms and hydrogen.

each G is independently a monovalent or polyvalent group derived by substitution of alkyl, alkenyl, aryl or aralkyl wherein G can contain from 1 to 18 carbon atoms, with the proviso that G is not such that the silane would contain an α,β -unsaturated carbonyl including a carbon-carbon double bond next to the thiocarbonyl group, and if G is univalent, G can be a hydrogen atom;

X is independently a group selected from the group consisting of -Cl, -Br, RO-, $\text{RC}(=\text{O})\text{O-}$, $\text{R}_2\text{C}=\text{NO-}$, $\text{R}_2\text{NO-}$ or $\text{R}_2\text{N-}$, -R, $(\text{OSiR}_2)_l(\text{OSiR}_3)$ wherein each R is as above and at least one X is not -R;

Q is oxygen, sulfur or (-NR-);

A is carbon, sulfur, phosphorus, or sulfonyl;

E is oxygen, sulfur or NR;

p is 0 to 5; r is 1 to 3; z is 0 to 2; q is 0 to 6; a is 0 to 7; b is 1 to 3; j is 0 to 1, but it may be 0 only if p is 1, c is 1 to 6, t is 0 to 5; s is 1 to 3; k is 1 to 2, with the provisos that (A) if A is carbon, sulfur or sulfonyl, then (i) $a + b = 2$ and (ii) $k = 1$; (B) if A is phosphorus, then $a + b = 3$ unless both (i) $c > 1$ and (ii) $b = 1$, in which case $a = c + 1$; and (C) if A is phosphorus, then k is 2.

3. A process according to claim 1 or 2 wherein the mercaptosilane is selected from the group consisting of 2-triethoxysilyl-1-ethyl thioacetate; 2-trimethoxysilyl-1-ethyl thioacetate; 2-(methyldimethoxysilyl)-1-ethyl thioacetate; 3-trimethoxysilyl-1-propyl thioacetate; triethoxysilylmethyl thioacetate; trimethoxysilylmethyl thioacetate; triisopropoxysilylmethyl thioacetate; methyldiethoxysilylmethyl thioacetate; methyldimethoxysilylmethyl thioacetate; methyldiisopropoxysilylmethyl thioacetate; dimethylethoxysilylmethyl thioacetate; dimethylmethoxysilylmethyl thioacetate; dimethylisopropoxysilylmethyl thioacetate; 2-triisopropoxysilyl-1-ethyl thioacetate; 2-(methyldiethoxysilyl)-1-ethyl thioacetate; 2-(methyldiisopropoxysilyl)-1-ethyl thioacetate; 2-(dimethylethoxysilyl)-1-ethyl thioacetate; 2-(dimethylmethoxysilyl)-1-ethyl thioacetate; 2-(dimethylisopropoxysilyl)-1-ethyl thioacetate; 3-triethoxysilyl-1-propyl thioacetate; 3-triisopropoxysilyl-1-propyl thioacetate; 3-methyldiethoxysilyl-1-propyl thioacetate; 3-methyldimethoxysilyl-1-propyl thioacetate; 3-methyldiisopropoxysilyl-1-propyl thioacetate; 1-(2-triethoxysilyl-1-ethyl)-4-thioacetylcyclohexane; 1-(2-triethoxysilyl-1-ethyl)-3-thioacetylcyclohexane; 2-triethoxysilyl-5-thioacetylnorbornene; 2-triethoxysilyl-4-thioacetylnorbornene; 2-(2-triethoxysilyl-1-ethyl)-5-thioacetylnorbornene; 2-(2-triethoxysilyl-1-ethyl)-4-thioacetylnorbornene; 1-(1-oxo-2-thia-5-triethoxysilylpentyl)benzoic acid; 6-triethoxysilyl-1-hexyl thioacetate; 1-triethoxysilyl-5-hexyl thioacetate; 8-triethoxysilyl-1-octyl thioacetate; 1-triethoxysilyl-7-octyl thioacetate; 6-triethoxysilyl-1-hexyl thioacetate; 1-triethoxysilyl-5-octyl thioacetate; 8-trimethoxysilyl-1-octyl thioacetate; 1-trimethoxysilyl-7-octyl thioacetate; 10-triethoxysilyl-1-decyl thioacetate; 1-triethoxysilyl-9-decyl thioacetate; 1-triethoxysilyl-2-butyl thioacetate; 1-triethoxysilyl-3-butyl thioacetate; 1-triethoxysilyl-3-methyl-2-butyl thioacetate; 1-triethoxysilyl-3-methyl-3-butyl thioacetate; 3-trimethoxysilyl-1-propyl thiooctanoate; 3-triethoxysilyl-1-propyl thiopalmitate; 3-triethoxysilyl-1-propyl thiooctanoate; 3-triethoxysilyl-1-propyl thiobenzoate; 3-triethoxysilyl-1-propyl thio-2-ethylhexanoate; 3-methyldiacetoxysilyl-1-propyl thioacetate; 3-triacetoxysilyl-1-propyl thioacetate; 2-methyldiacetoxysilyl-1-ethyl thioacetate; 2-triacetoxysilyl-1-ethyl thioacetate; 1-methyldiacetoxysilyl-1-ethyl thioacetate; 1-triacetoxysilyl-1-ethyl thioacetate; tris-(3-triethoxysilyl-1-propyl)trithiophosphate; bis-(3-triethoxysilyl-1-propyl)methyldithiophosphonate; bis-(3-triethoxysilyl-1-propyl)ethyldithiophosphonate; 3-triethoxysilyl-1-propyldimethylthiophosphinate; 3-triethoxysilyl-1-propyldiethylthiophosphinate; tris-(3-triethoxysilyl-1-propyl)tetrathio-phosphate; bis-(3-triethoxysilyl-1-propyl)methyltrithiophosphonate; bis-(3-triethoxysilyl-1-propyl)ethyltrithiophosphonate; 3-triethoxysilyl-1-propyldimethyldithiophosphinate; 3-triethoxysilyl-1-propyldiethyldithiophosphinate; tris-(3-methyldimethoxysilyl-1-propyl)trithiophosphate; bis-(3-methyldimethoxysilyl-1-propyl)methyldithiophosphonate; bis-(3-methyldimethoxysilyl-1-propyl)ethyldithiophosphonate; 3-methyldimethoxysilyl-1-propyldimethyl-

thiophosphate; 3-methyldimethoxysilyl-1-propyldiethylthiophosphate; 3-triethoxysilyl-1-propylmethylthiosulphate; 3-triethoxysilyl-1-propylmethanethiosulphonate; 3-triethoxysilyl-1-propylethanethiosulphonate; 3-triethoxysilyl-1-propylbenzenethiosulphonate; 3-triethoxysilyl-1-propyltoluenethiosulphonate; 3-triethoxysilyl-1-propylnaphthalenethiosulphonate; 3-triethoxysilyl-1-propylxilenethiosulphonate; triethoxysilylmethylmethylthiosulphate; triethoxysilylmethylmethanethiosulphonate; triethoxysilylmethylethanethiosulphonate; triethoxysilylmethylbenzenethiosulphonate; triethoxysilylmethyltoluenethiosulphonate; triethoxysilylmethylnaphthalenethiosulphonate; triethoxysilylmethylxilenethiosulphonate.

4. A process according to claim 1 wherein Y is $-C(=O)-$.

5. A process according to claim 4 wherein each X is $RO-$, the silane is of formula (1), $r = 1$ and $s = 1$.

Patentansprüche

1. Verfahren zur Herstellung eines gefüllten Kautschuks, umfassend:

- a. Mischen eines Kautschuks, eines blockierten Mercaptosilans und eines anorganischen Füllstoffes;
- b. Einmischen in die Mischung von Schritt (a) eines Deblockierungsmittels, um das Mercaptosilari zu deblockieren, und eines Härtungsmittels in die Mischung;
- und
- c. Härtenlassen der Mischung.

2. Verfahren nach Anspruch 1, in dem das Mercaptosilan ausgewählt ist aus der Gruppe bestehend aus:



und



worin

Y eine mehrwertige Spezies $(\text{Q})_2\text{A}(=\text{E})$ ist, worin jeweils das Atom (A), das an das ungesättigte Heteroatom (E) gebunden ist, an den Schwefel gebunden ist, welcher wiederum über eine Gruppe G mit dem Siliciumatom verknüpft ist;

jedes R unabhängig ausgewählt ist aus geraden, cyclischen oder verzweigten Alkyl-, Alkenylgruppen, Arylgruppen und Aralkylgruppen, wobei jedes R 1 bis 18 Kohlenstoffatome enthält, und Wasserstoff.

jedes G unabhängig eine einwertige oder mehrwertige Gruppe ist, die durch Substitution von Alkyl, Alkenyl, Aryl oder Aralkyl abgeleitet ist, wobei G 1 bis 18 Kohlenstoffatome enthalten kann, mit der Maßgabe, dass G nicht derart ist, dass das Silan ein α,β -ungesättigtes Carbonyl, einschließlich einer Kohlenstoff-Kohlenstoff-Doppelbindung in Nachbarschaft zu der Thiocarbonylgruppe, enthalten würde, und G, falls G einwertig ist, ein Wasserstoffatom sein kann;

X unabhängig eine Gruppe ist, die ausgewählt ist aus der Gruppe bestehend aus $-\text{Cl}$, $-\text{Br}$, $\text{RO}-$, $\text{RC}(=\text{O})\text{O}-$, $\text{R}_2\text{C}=\text{NO}-$, $\text{R}_2\text{NO}-$ oder $\text{R}_2\text{N}-$, $-\text{R}$, $-(\text{OSiR}_2)_t(\text{OSiR}_3)$, worin jedes R wie oben ist und mindestens ein X nicht $-\text{R}$ ist; Q Sauerstoff, Schwefel oder $(-\text{NR}-)$ ist;

A Kohlenstoff, Schwefel, Phosphor oder Sulfonyl ist;

E Sauerstoff, Schwefel oder NR ist;

p für 0 bis 5 steht; r für 1 bis 3 steht; z für 0 bis 2 steht; q für 0 bis 6 steht; a für 0 bis 7 steht; b für 1 bis 3 steht; j für 0 bis 1 steht, wobei es 0 jedoch nur dann sein kann, wenn p für 1 steht, c für 1 bis 6 steht, t für 0 bis 5 steht; s für 1 bis 3 steht, k für 1 bis 2 steht, mit den Maßgaben, dass (A), falls A Kohlenstoff, Schwefel oder Sulfonyl ist, dann (i) $a + b = 2$ und (ii) $k = 1$; (B), falls A Phosphor ist, dann $a + b = 3$, falls nicht sowohl (i) $c > 1$ als auch (ii) $b = 1$, in welchem Fall $a = c + 1$; und (C), falls A Phosphor ist, dann k für 2 steht.

3. Verfahren nach Anspruch 1 oder 2, in dem das Mercaptosilan ausgewählt ist aus der Gruppe bestehend aus 2-Triethoxysilyl-1-ethylthioacetat; 2-Trimethoxysilyl-1-ethylthioacetat; 2-(Methyldimethoxysilyl)-1-ethylthioacetat;

3-Trimethoxysilyl-1-propylthioacetat; Triethoxysilylmethylthioacetat; Trimethoxysilylmethylthioacetat; Triisopropoxysilylmethylthioacetat; Methyl-diethoxysilylmethylthioacetat; Methyl-dimethoxysilylmethylthioacetat; Methyl-diisopropoxysilylmethylthioacetat; Dimethylethoxysilylmethylthioacetat; Dimethylmethoxysilylmethylthioacetat; Dimethylisopropoxysilylmethylthioacetat; 2-Triisopropoxysilyl-1-ethylthioacetat; 2-(Methyl-diethoxysilyl)-1-ethylthioacetat; 2-(Methyl-diisopropoxysilyl)-1-ethylthioacetat; 2-(Dimethylethoxysilyl)-1-ethylthioacetat; 2-(Dimethylmethoxysilyl)-1-ethylthioacetat; 2-(Dimethylisopropoxysilyl)-1-ethylthioacetat; 3-Triethoxysilyl-1-propylthioacetat; 3-Triisopropoxysilyl-1-propylthioacetat; 3-Methyl-diethoxysilyl-1-propylthioacetat; 3-Methyl-dimethoxysilyl-1-propylthioacetat; 3-Methyl-diisopropoxysilyl-1-propylthioacetat; 1-(2-Triethoxysilyl-1-ethyl)-4-thioacetylcyclohexan; 1-(2-Triethoxysilyl-1-ethyl)-3-thioacetylcyclohexan; 2-Triethoxysilyl-5-thioacetylnorbornen; 2-Triethoxysilyl-4-thioacetylnorbornen; 2-(2-Triethoxysilyl-1-ethyl)-5-thioacetylnorbornen; 2-(2-Triethoxysilyl-1-ethyl)-4-thioacetylnorbornen; 1-(1-Oxo-2-thia-5-triethoxysilylpentyl)benzoesäure; 6-Triethoxysilyl-1-hexylthioacetat; 1-Triethoxysilyl-5-hexylthioacetat; 8-Triethoxysilyl-1-octylthioacetat; 1-Triethoxysilyl-7-octylthioacetat; 6-Triethoxysilyl-1-hexylthioacetat; 1-Triethoxysilyl-5-octylthioacetat; 8-Trimethoxysilyl-1-octylthioacetat; 1-Trimethoxysilyl-7-octylthioacetat; 10-Triethoxysilyl-1-decylthioacetat; 1-Triethoxysilyl-9-decylthioacetat; 1-Triethoxysilyl-2-butylthioacetat; 1-Triethoxysilyl-3-butylthioacetat; 1-Triethoxysilyl-3-methyl-2-butylthioacetat; 1-Triethoxysilyl-3-methyl-3-butylthioacetat; 3-Trimethoxysilyl-1-propylthiooctanoat; 3-Triethoxysilyl-1-propylthiopalmat; 3-Triethoxysilyl-1-propylthiooctanoat; 3-Triethoxysilyl-1-propylthiobenzoat; 3-Triethoxysilyl-1-propylthio-2-ethylhexanoat; 3-Methyldiacetoxysilyl-1-propylthioacetat; 3-Triacetoxysilyl-1-propylthioacetat; 2-Methyldiacetoxysilyl-1-ethylthioacetat; 2-Triacetoxysilyl-1-ethylthioacetat; 1-Methyldiacetoxysilyl-1-ethylthioacetat; 1-Triacetoxysilyl-1-ethylthioacetat; Tris(3-triethoxysilyl-1-propyl)trithiophosphat; Bis(3-triethoxysilyl-1-propyl)-methyldithiophosphonat; Bis(3-triethoxysilyl-1-propyl)ethyldithiophosphonat; 3-Triethoxysilyl-1-propyldimethyldithiophosphinat; 3-Triethoxysilyl-1-propyldiethylthiophosphinat; Tris(3-triethoxysilyl-1-propyl)tetrathiophosphat; Bis(3-triethoxysilyl-1-propyl)methyltrithiophosphonat; Bis(3-triethoxysilyl-1-propyl)ethyltrithiophosphonat; 3-Triethoxysilyl-1-propyldimethyldithiophosphinat; 3-Triethoxysilyl-1-propyldiethylthiophosphinat; Tris(3-methyldimethoxysilyl-1-propyl)trithiophosphat; Bis(3-methyldimethoxysilyl-1-propyl)methyldithiophosphonat; Bis(3-methyldimethoxysilyl-1-propyl)ethyldithiophosphonat; 3-Methyldimethoxysilyl-1-propyldimethyldithiophosphinat; 3-Methyldimethoxysilyl-1-propyldiethylthiophosphinat; 3-Triethoxysilyl-1-propylmethylthiosulfat; 3-Triethoxysilyl-1-propylmethanthiosulfonat; 3-Triethoxysilyl-1-propylethanthiosulfonat; 3-Triethoxysilyl-1-propylbenzothiosulfonat; 3-Triethoxysilyl-1-propyltoluolthiosulfonat; 3-Triethoxysilyl-1-propylnaphthalinthiosulfonat; 3-Triethoxysilyl-1-propylxylolthiosulfonat; Triethoxysilylmethylmethanthiosulfat; Triethoxysilylmethylmethanthiosulfonat; Triethoxysilylmethylethanthiosulfonat; Triethoxysilylmethylbenzothiosulfonat; Triethoxysilylmethyltoluolthiosulfonat; Triethoxysilylmethylnaphthalinthiosulfonat; Triethoxysilylmethylxylolthiosulfonat.

4. Verfahren nach Anspruch 1, in dem Y für -C(=O)- steht.

5. Verfahren nach Anspruch 4, in dem jedes X für RO- steht, das Silan die Formel (1) aufweist, $r = 1$ und $s = 1$.

Revendications

1. Procédé pour la fabrication d'un caoutchouc chargé, comprenant:

- le mélange d'un caoutchouc d'un mercaptosilane bloqué et d'une charge inorganique;
- le mélange, dans le mélange de l'étape (a), d'un agent 'de déblocage au mélange pour 'débloquer le mercaptosilane et un agent de durcissement; et
- le durcissement du mélange.

2. Procédé selon la revendication 1, où le mercaptosilane est sélectionné dans le groupe consistant en:



et



où

Y est une espèce polyvalente $(Q)_zA(=E)$, chacun où l'atome (A) attaché à l'hétéroatome insaturé (E) est attaché au soufre, qui à son tour est enchaîné via un groupe G à l'atome de silicium;

chaque R est choisi indépendamment parmi alkyle droit, cyclique ou ramifié, des groupes alcényle, des groupes aryle et des groupes aralkyle, avec chaque R contenant de 1 à 18 atomes de carbone et hydrogène.

chaque G est indépendamment un groupe monovalent ou polyvalent dérivé par substitution d'alkyle, alcényle, aryle ou aralkyle, où G peut contenir de 1 à 18 atomes de carbone, à condition que G ne soit pas tel que le silane puisse contenir un carbonyle α,β -insaturé contenant une double liaison carbone-carbone proche du groupe thiocarbonyle, et si G est univalent, G peut être un atome d'hydrogène;

X est indépendamment un groupe sélectionné dans le groupe consistant en $-Cl$, $-Br$, $RO-$, $RC(=O)O-$, $R_2C=NO-$, R_2NO- ou R_2N- , $-R$, $-(OSiR_2)_2(OSiR_3)$, où chaque R est comme ci-dessus et au moins un X n'est pas $-R$;

Q est oxygène, soufre ou $(-NR-)$;

A est carbone, soufre, phosphore ou sulfonyle;

E est oxygène, soufre ou NR;

p est 0 à 5; r est 1 à 3; z est 0 à 2; q est 0 à 6; a est 0 à 7; b est 1 à 3; j est 0 à 1, mais il peut être 0 uniquement si p est 1, c est 1 à 6, t est 0 à 5; s est 1 à 3; k est 1 à 2, aux conditions que (A) si A est carbone, soufre ou sulfonyle, alors (i) $a + b = 2$ et (ii) $k = 1$; (B) si A est phosphore, alors $a + b = 3$, à moins que (i) $c > 1$ et (ii) $b = 1$, auquel cas $a = c + 1$; et (C) si A est phosphore, alors k est 2.

3. Procédé selon la revendication 1 ou la revendication 2, où le mercaptosilane est sélectionné dans le groupe consistant en

2-triéthoxysilyl-1-éthyl thioacétate; 2-triméthoxysilyl-1-éthyl thioacétate; 2-(méthylidiméthoxysilyl)-1-éthyl thioacétate; 3-triméthoxysilyl-1-propyl thioacétate; triéthoxysilylméthyl thioacétate; triméthoxysilylméthyl thioacétate; triisopropoxysilylméthyl thioacétate; méthylidiéthoxysilylméthyl thioacétate; méthylidiméthoxysilylméthyl thioacétate; méthylidiisopropoxysilylméthyl thioacétate; diméthyléthoxysilylméthyl thioacétate; diméthylméthoxysilylméthyl thioacétate; diméthylisopropoxysilylméthyl thioacétate; 2-triisopropoxysilyl-1-éthyl thioacétate; 2-(méthylidéthoxysilyl)-1-éthyl thioacétate; 2-(méthylidiisopropoxysilyl)-1-éthyl thioacétate; 2-(diméthyléthoxysilyl)-1-éthyl thioacétate; 2-(diméthylméthoxysilyl)-1-éthyl thioacétate; 2-(diméthylisopropoxysilyl)-1-éthyl thioacétate; 3-triéthoxysilyl-1-propyl thioacétate; 3-triisopropoxysilyl-1-propyl thioacétate; 3-méthylidiéthoxysilyl-1-propyl thioacétate; 3-méthylidiméthoxysilyl-1-propyl thioacétate; 3-méthylidiisopropoxysilyl-1-propyl thioacétate; 1-(2-triéthoxysilyl-1-éthyl)-4-thioacétylcyclohexane; 1-(2-triéthoxysilyl-1-éthyl)-3-thioacétylcyclohexane; 2-triéthoxysilyl-5-thioacétylnorbornène; 2-triéthoxysilyl-4-thioacétylnorbornène; 2-(2-triéthoxysilyl-1-éthyl)-5-thioacétylnorbornène; 2-(2-triéthoxysilyl-1-éthyl)-4-thioacétylnorbornène; acide 1-(1-oxo-2-thia-5-thiéthoxysilylpentyl) benzoïque; 6-triéthoxysilyl-1-hexyl thioacétate; 1-triéthoxysilyl-5-hexyl thioacétate; 8-triéthoxysilyl-1-octyl thioacétate; 1-triéthoxysilyl-7-octyl thioacétate; 6-triéthoxysilyl-1-hexyl thioacétate; 1-triéthoxysilyl-5-octyl thioacétate; 8-triméthoxysilyl-1-octyl thioacétate; 1-triméthoxysilyl-7-octyl thioacétate; 10-triéthoxysilyl-1-decyl thioacétate; 1-triéthoxysilyl-9-decyl thioacétate; 1-triéthoxysilyl-2-butyl thioacétate; 1-triéthoxysilyl-3-butyl thioacétate; 1-triéthoxysilyl-3-méthyl-2-butyl thioacétate; 1-triéthoxysilyl-3-méthyl-3-butyl thioacétate; 3-triméthoxysilyl-1-propyl thiooctanoate; 3-triéthoxysilyl-1-propyl thiopalmitate; 3-triéthoxysilyl-1-propyl thiooctanoate; 3-triéthoxysilyl-1-propyl thiobenzoate; 3-triéthoxysilyl-1-propyl thio-2-éthylhexanoate; 3-méthylidiacétoxysilyl-1-propyl thioacétate; 3-triacétoxysilyl-1-propyl thioacétate; 2-méthylidiacétoxysilyl-1-éthyl thioacétate; 2-triacétoxysilyl-1-éthyl thioacétate; 1-méthylidiacétoxysilyl-1-éthyl thioacétate; 1-triacétoxysilyl-1-éthyl thioacétate; tris-(3-triéthoxysilyl-1-propyl)trithiophosphate; bis-(3-triéthoxysilyl-1-propyl)méthylidithiophosphonate; bis-(3-triéthoxysilyl-1-propyl)éthylidithiophosphonate; 3-triéthoxysilyl-1-propyldiméthylthiophosphinate; 3-triéthoxysilyl-1-propyldiéthylthiophosphinate; tris-(3-triéthoxysilyl-1-propyl)tetrathiophosphate; bis-(3-triéthoxysilyl-1-propyl)méthyltrithiophosphonate; bis-(3-triéthoxysilyl-1-propyl)éthyltrithiophosphonate; 3-triéthoxysilyl-1-propyldiméthylidithiophosphinate; 3-triéthoxysilyl-1-propyldiéthylidithiophosphinate; tris-(3-méthylidiméthoxysilyl-1-propyl)trithiophosphate; bis-(3-méthylidiméthoxysilyl-1-propyl)méthylidithiophosphonate; bis-(3-méthylidiméthoxysilyl-1-propyl)éthylidithiophosphonate; 3-méthylidiméthoxysilyl-1-propyldiméthylthiophosphinate; 3-méthylidiméthoxysilyl-1-propyldiéthylthiophosphinate; 3-triéthoxysilyl-1-propylméthylthiosulphate; 3-triéthoxysilyl-1-propylméthanethiosulphonate; 3-triéthoxysilyl-1-propyléthanethiosulphonate; 3-triéthoxysilyl-1-propylbenzèthiosulphonate; 3-triéthoxysilyl-1-propyltoluèthiosulphonate; 3-triéthoxysilyl-1-propylnaphthalèthiosulphonate; 3-triéthoxysilyl-1-propylxylèthiosulphonate; triéthoxysilylméthylméthylthiosulphate; triéthoxysilylméthylméthanethiosulphonate; triéthoxysilylméthyléthanethiosulphonate; triéthoxysilylméthylbenzèthiosulphonate; triéthoxysilylméthyltoluèthiosulphonate; triéthoxysilylméthylnaphthalèthiosulphonate; triéthoxysilylméthylxylèthiosulphonate.

4. Procédé selon la revendication 1, où Y est $-C(=O)-$.

5. Procédé selon la revendication 4, où chaque X est $RO-$, le silane est de la formule (1), $r = 1$ et $s = 1$.